



Standard Specification for Supplemental Coolant Additives (SCAs) for Use in Precharging Coolants for Heavy-Duty Engines¹

This standard is issued under the fixed designation D 5752; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the general, physical, chemical, and performance requirements for Supplemental Coolant Additives (SCAs) at a precharged level in the cooling systems of heavy-duty engines.

NOTE 1—After precharging, SCAs are customarily used periodically to service cooling systems at $\frac{1}{4}$ to $\frac{1}{3}$ the precharged dosage to compensate for additives lost through dilution and depletion.

1.2 The SCA products meeting this specification are intended for use with water or recommended dilutions of coolant concentrates or prediluted engine coolants. Engine coolant products shall be of the low-silicate type and, if ethylene glycol based, shall meet Specification D 4985. Propylene glycol base low-silicate-type coolant products may also be used, if these materials meet the chemical and performance requirements of Specification D 4985.

1.3 The SCA concentrate before dissolution may be in either liquid, solid, or slurry form. The form is as agreed upon between the manufacturer and the user.

1.4 The values stated in SI units are to be regarded as standard. The inch-pound units in parentheses are approximate equivalents provided for information only.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. Specific precautionary statements are given in 4.1.*

2. Referenced Documents

2.1 ASTM Standards:²

D 512 Test Method for Chloride Ion in Water

D 516 Test Method for Sulfate Ion in Water

D 1119 Test Method for Ash Content of Engine Coolants and Antirusts

D 1121 Test Method for Reserve Alkalinity of Engine Coolants and Antirusts

D 1126 Test Method for Hardness of Water

D 1193 Specification for Reagent Water

D 1287 Test Method for pH of Engine Coolants and Antirusts

D 1293 Test Methods for pH of Water

D 1384 Test Method for Corrosion Test for Engine Coolants in Glassware

D 1881 Test Method for Foaming Tendencies of Engine Coolants in Glassware

D 1882 Test Method for Effect of Cooling System Chemical Solutions on Organic Finishes for Automotive Vehicles

D 1888 Test Methods for Particulate and Dissolved Matter in Water

D 2570 Test Method for Simulated Service Corrosion Testing of Engine Coolants

D 2809 Test Method for Cavitation Corrosion and Erosion-Corrosion Characteristics of Aluminum Pumps with Engine Coolants

D 3634 Test Method for Trace Chloride Ion in Engine Coolants

D 4327 Test Method for Anions in Water by Chemically Suppressed Ion Chromatography

D 4340 Test Method for Corrosion of Cast Aluminum Alloys in Engine Coolants Under Heat-Rejecting Conditions

D 4985 Specification for Low Silicate Ethylene Glycol Base Engine Coolant for Heavy Duty Engines Requiring an Initial Charge of Supplemental Coolant Additive (SCA)

D 5827 Test Method for Analysis of Engine Coolant for Chloride and Other Anions by Ion Chromatography

D 5828 Test Method for Compatibility of Supplemental Coolant Additives (SCAs) and Engine Coolant Concentrates

D 6129 Test Method for Silicon in Engine Coolant Concentrates by Atomic Absorption Spectroscopy

D 6130 Test Method for the Determination of Silicon and Other Elements in Engine Coolant by Inductively Coupled Plasma-Atomic Emission Spectroscopy

¹ This specification is under the jurisdiction of ASTM Committee D15 on Engine Coolants and is the direct responsibility of Subcommittee D15.07 on Specifications.

Current edition approved May 1, 2004. Published June 2004. Originally approved in 1995. Last previous edition approved in 1998 as D 5752 - 98.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

D 6471 Specification for Recycled Prediluted Aqueous Glycol Base Engine Coolant (50 % Minimum) for Automobile and Light-Duty Service

D 6472 Specification for Recycled Glycol Base Engine Coolant Concentrate for Automobile and Light-Duty Service

E 1177 Specification for Engine Coolant Grade Glycol

G 32 Test Method for Cavitation Erosion Using Vibratory Apparatus

3. General Requirements

3.1 The SCA concentrate upon addition to water or water/glycol mixtures at the SCA manufacturer's recommended addition level shall provide, excepting freeze and boil protection, the same performance as coolants meeting Specification D 4985.

3.2 Liquid SCA concentrates shall be storable in the manufacturer's original container at temperatures from -7 to $+55^{\circ}\text{C}$ (20 to 130°F) without chemical change. Any precipitation of ingredients evidenced by the dropout of solid material or liquid turbidity shall disappear upon agitation and warming of the solution to a temperature exceeding 2°C (35°F).

3.3 Solid, slurry, and paste forms of SCA concentrate shall be so formulated and packaged as to prevent chemical or physical change during storage before use. This requirement applies to storage temperatures of -7 to $+55^{\circ}\text{C}$ (20 to 130°F), regardless of humidity.

3.4 The SCA concentrates, when used according to the manufacturer's recommendations, shall dissolve totally in the test solutions required in this specification. A light haze is permitted.

3.5 If an engine, vehicle, or servicing organization recommends adding an SCA product to a fully formulated coolant, the recommending organization assumes responsibility for determining the compatibility and conducting suitable tests. ASTM has developed a compatibility test (Test Method D 5828), which may be used. At the present time, it is recommended that SCAs be used only in conjunction with coolant products meeting Specification D 4985.

4. Preparation of Test Solutions

4.1 The preparation of test solutions for this specification is listed in Table 1. Where ethylene glycol is required, it shall meet Specification E 1177. Where distilled water is required, it shall conform to Type IV of Specification D 1193. If propylene glycol is to be used to meet the requirements of this specification as established in Table 1 and Table 2, the propylene glycol shall also meet Specification E 1177. (**Warning**—Propylene glycol base coolants have not been extensively tested for precharging with an SCA, and therefore, the effect of different glycol products on property performance is not well established.)

4.2 The quantity of any freshly prepared test solution required in this specification shall be sufficient to perform the specific tests. However, no test solution shall be stored longer than 96 h before initiation of a specific procedure.

TABLE 1 Composition of Test Solutions for Table 2 Performance Requirements^A

Test Method	SCA Concentrate	Solvent Mixture
D 1384	one-half manufacturer's recommended precharged level	standard corrosive water ^B
D 1384	three times manufacturer's recommended precharged level	33 vol % ethylene glycol in standard corrosive water ^{B,C}
D 1881	manufacturer's recommended precharge level	33 vol % ethylene glycol in standard corrosive water ^{B,C}
D 2570	manufacturer's recommended precharge level	44 vol % ethylene glycol in standard corrosive water ^{B,C}
D 2809	manufacturer's recommended precharge level	16.7 vol % ethylene glycol in standard corrosive water ^{B,C}
D 4340	manufacturer's recommended precharge level	165-mg/L NaCl dissolved in a 1-L solution of 25 vol % ethylene glycol in deionized water ^{C,D}

^ATest solution to be prepared according to Section 4.

^BSee Section 7 of Test Method D 2570 for composition and method of preparation of standard corrosive water.

^CEthylene glycol shall meet Specification E 1177. If propylene glycol is used as an alternate to ethylene glycol, the propylene glycol shall also meet Specification E 1177. (See **Warning** in 4.1.)

^DWater conforming to Type IV of Specification D 1193 is acceptable.

TABLE 2 Performance Requirements^A

Property	Specific Values	Test Method
Corrosion in glassware mass loss, mg/specimen		D 1384
Copper	10 max	
Solder	30 max	
Brass	10 max	
Steel	10 max	
Cast iron	10 max	
Aluminum	30 max	
Simulated service test mass loss, mg/specimen		D 2570
Copper	20 max	
Solder	60 max	
Brass	20 max	
Steel	20 max	
Cast iron	20 max	
Aluminum	60 max	
Foaming		D 1881
Volume, mL	150 max	
Break time, s	5 max	
Water pump cavitation erosion-corrosion rating	8 min	D 2809
Corrosion of cast aluminum alloys at heat-rejecting surfaces, mg/cm ² /week	1.0 max	D 4340
Ultrasonic cavitation resistance	see Annex A1	under development
SCA-glycol base coolant compatibility	^B	D 5828
Hot surface scaling and deposits resistance ^C	...	under development

^ATest solutions for use in meeting Table 2 performance requirements are to be prepared according to Table 1.

^BSCA products may be required to meet a compatibility requirement. Although Test Method D 5828 has been developed, ASTM has not established allowable limits. Until allowable limits have been approved, an agreement must be established between the SCA manufacturer and engine or vehicle user. This agreement shall include a definition of the test procedure, acceptable equipment, and the performance rating criteria.

^CSee Appendix X2 for additional information.

5. Detailed Requirements

5.1 Test solutions prepared according to Table 1 shall meet the performance requirements in Table 2, the general requirements in Table 3, and the physical and chemical requirements in Table 4.

TABLE 3 General Requirements

Property	Specific Value	Test Method
Effect on nonmetals ^A	no adverse effect	under consideration
Storage stability	see 3.2 and 3.3	...

^AEvaluate using the SCA concentrate at the manufacturer's recommended precharge level in a 50:50 volume mixture of distilled water and ethylene glycol or distilled water and propylene glycol, each glycol conforming to Specification E 1177.

5.2 The SCAs shall additionally provide added protection in operating engines against cavitation corrosion (also termed liner pitting) and against scaling of internal engine hot surfaces. Hot surfaces are typically within the engine head, head spacer, or liquid-cooled exhaust manifold. The American Society for Testing and Materials has test methods under development for both cavitation corrosion and hot surfaces scaling. Until these procedures are adopted as ASTM standards, the mandatory requirements of Annex A1 shall apply.

TABLE 4 Physical and Chemical Properties

Property ^A	Specific Values	Test Method
Ash content, dissolved in distilled water, mass, %	5 max	D 1119
pH, in distilled water	7.5 to 11.0	D 1287
Reserve alkalinity, in distilled water	report ^B	D 1121
Chloride ion, in distilled water, ppm	25 max	D 3634, D 5827
Silicon, in distilled water, ppm	250 max	D 6129, D 6130
Effect on vehicle finish	no effect ^C	D 1882

^AProperty must be met with the specified solution, at an SCA precharge addition level recommended by the SCA manufacturer. (This is usually 3 % by volume.)

^BValue agreed upon between the supplier and the customer.

^CCurrently, many heavy-duty engine manufacturers and vehicle manufacturers that use these engines prepare test panels using the specific paint finishes used on their actual products. Coolant product manufacturers and equipment builders should agree on the exact test procedures and acceptance criteria on an individual case basis.

6. Keywords

6.1 heavy-duty engine coolants; precharging heavy-duty engines; SCA; supplemental coolant additives

ANNEX

(Mandatory Information)

A1. CHEMICAL REQUIREMENTS FOR SCAs

A1.1 Test methods to determine cavitation corrosion resistance are under development. Several chemical compositions of SCAs have been extensively tested by producers and users and found to minimize satisfactorily cylinder liner cavitation in actual test engines. Until such time as an ASTM procedure is adopted that effectively evaluates cylinder liner cavitation corrosion, SCA formulations under this specification shall provide the following when used at the SCA manufacturer's recommended precharge addition level:

A1.1.1 A minimum concentration of nitrite as (NO_2^-) in the cooling system of 1200 ppm, or

A1.1.2 A minimum combined concentration of nitrite as (NO_2^-) plus molybdate as (MoO_4^{-2}) in the cooling system of 780 ppm. At least 300 ppm each of NO_2^- and MoO_4^{-2} must be present.

A1.1.3 Concentrations below these levels may not provide sufficient protection. (See X1.1.3.2 for further information.)

A1.2 Composition limits in A1.1 are waived provided:

A1.2.1 The SCA producer and engine manufacturer agree to specified composition limits for one or more chemical ingredients other than those stated in A1.1.

A1.2.2 Both parties agree to accept laboratory data or in-service performance experience demonstrating that the alternate composition exerts a positive influence on reducing cavitation corrosion in an operating engine.

A1.2.3 In-service qualification tests may consist of single- or multiple-cylinder engine tests. At the option of the engine or

vehicle manufacturer, such testing may be conducted in "loose engines" or in engines fully integrated into an application such as a vehicle, a power boat, or a stationary power source. One such test has been developed.³

A1.3 Chemical composition requirements for cavitation corrosion protection will be removed from this specification and replaced with an ASTM test method when a test method is developed and adopted.

A1.4 No specific chemical composition requirements for hot surface scaling and deposit resistance have been established at this time. A test procedure for this property is under development and will be incorporated into Table 2 when a procedure is approved by ASTM.

A1.5 Lack of compatibility between the coolant and SCA product's chemistry results in chemical ingredient dropout from solution, with potential adverse effects in the vehicle or engine cooling system. A test procedure for compatibility has been developed, Test Method D 5828, and may be used to establish compatibility between the coolant and the SCA product.

³ "A Comparison of Engine Coolant in an Accelerated Heavy-Duty Engine Cavitation Test," SAE Technical Paper 960883, SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

APPENDIXES

(Nonmandatory Information)

X1. COOLANT MAINTENANCE FOR HEAVY-DUTY ENGINES

X1.1 *Engine Coolant*—Cooling system fill for a heavy-duty engine consists of water, coolant concentrate (antifreeze), or prediluted engine coolant, and SCA.

X1.1.1 *Water:*

X1.1.1.1 Water quality affects the efficiency of coolant additives. When untreated, all water is corrosive. Water having a high mineral content or corrosive materials is unfit for cooling system use.

X1.1.1.2 When preparing coolant mixtures, the water should be of such quality that it does not contain excessive solids, hardness salts, sulfates, or chlorides. In the absence of specific recommendations from the engine or vehicle manufacturer, see Table X1.1. Contact your local water department, the responsible government agency, or submit a water sample for analyses if there is a question on water quality.

X1.1.2 *Coolant Concentrates:*

X1.1.2.1 SCAs may be used in conjunction with either ethylene glycol or propylene glycol base coolant concentrates, and in dilute versions of each. Ethylene glycol base coolant products should meet ASTM Specifications D 4985. ASTM specifications have not been established for low-silicate propylene glycol base coolants for heavy-duty engines requiring a precharge of SCAs. However, such products are available in the marketplace.

X1.1.2.2 The coolant concentration (antifreeze) should be maintained between 40 and 60 % by volume, depending on the engine operating environment. Freeze protection will be provided according to the following:

Glycol Content, %	Freeze Protection Temperature, °C (°F)	
	Ethylene Glycol	Propylene Glycol
40	-24 (-12)	-21 (-6)
50	-37 (-34)	-33 (-27)
60	-52 (-62)	-49 (-56)

NOTE X1.1—Coolant Specification D 4985 was developed based on the knowledge of the performance of engine coolants and their ingredients prepared from virgin materials. As such, these specifications do not address the potential effects, if any, of residual contaminants that could have been introduced if the coolants were prepared from recycled or reprocessed used automotive coolants or industrial glycol materials.

X1.1.2.3 The ASTM Committee on Engine Coolants is in the process of investigating the effect(s) of potential contaminants, if not removed in the reprocessing cycle, and has established standard specifications for reprocessed or recycled coolants (Specifications D 6471 and D 6472). It is desirable

that users of coolant products be fully advised when any coolant has been produced from reprocessed materials.

X1.1.3 *Supplemental Coolant Additive:*

X1.1.3.1 The SCAs are used to provide additional protection against deposits, corrosion, and pitting which may not be provided by the additives in the coolant concentrate or prediluted engine coolant. SCAs also extend the life of the coolant by adding to and replenishing the additives that deplete during normal operation. The SCAs, however, do not extend the freeze protection provided by the coolant concentrate.

X1.1.3.2 Heavy-duty engine users' experience has shown that SCA compositions below those defined in A1.1 may not provide long-term protection against cavitation corrosion (liner pitting). User experience and published information shows the presence of nitrite (NO₂⁻) in an SCA is particularly effective in providing maximum protection.

X1.1.3.3 New technology consisting of other chemistries may provide satisfactory protection. Such chemistries can be established for those listed in A1.1 by agreement between the producers and the users upon demonstration of performance. Such demonstrations can consist of comparative laboratory cavitation tests or comparative damage rating from testing in operating engines. One or both of these options may be applied in accordance with a specific agreement between parties.

X1.1.3.4 These evaluations shall be at the SCA manufacturer's recommended precharge concentration in diluted, low-silicate coolant concentrates.

X1.1.3.5 The SCAs should not be stored below 7°C (120°F) or above 55°C (130°F). Temperatures below -7°C (20°F) can lead, in liquid SCAs, to crystallization of components and nonhomogeneity in large containers. Temperatures above 55°C (130°F) may cause chemical changes that render the product unsuitable for use.

X1.2 *Coolant Maintenance Recommendations:*

X1.2.1 If any of the following recommendations differ, follow the engine or vehicle manufacturer's recommendations.

X1.2.2 Use coolant concentration recommended in this specification.

X1.2.3 Drain and flush the cooling system as recommended by the engine or vehicle manufacturer, or every two years, whichever occurs first.

X1.2.4 Follow the engine or vehicle manufacturer's recommendations for SCA precharging of the cooling system after draining and flushing.

X1.2.5 Use water that meets the requirement in Table X1.1.

X1.2.6 Use accurate, reliable equipment such as a refractometer to measure coolant concentrate levels for freeze protections.

X1.2.7 Use the SCA manufacturer's recommended test kit when testing the coolant for proper additive concentration. Test kits shall indicate the degree of liner pitting protection present in the coolant.

TABLE X1.1 Suggested Water Quality Limits^A

Property	Specific Values	Test Method
Total solids, ppm (grns/gal)	340 (20) max	D 1888
Total hardness, ppm (grns/gal)	170 (10) max	D 1126
Chloride (Cl), ppm (grns/gal)	40 (2.4) max	D 512, D 4327
Sulfate (SO ₄), ppm (grns/gal)	100 (5.9) max	D 516, D 4327
pH	5.5 to 9.0	D 1293

^AAdopted from a survey by the Committee D15 Water Quality Task Force.

X1.2.8 Check freezing point at two different levels when coolant concentrate and water is premixed and stored in bulk or drums to be sure mixing is complete before use.

X1.2.9 Use coolant mixed at the desired proportions for makeup.

X1.2.10 Use SCAs at recommended dosage to control deposits, corrosion, water pump damage, and pitting.

X1.2.11 Periodically check bulk premixed coolant storage tanks for separation of chemicals and contamination.

X1.2.12 DO NOT add undiluted coolant concentrate as makeup coolant.

X1.2.13 DO NOT add plain water as makeup coolant.

X1.2.14 DO NOT exceed 60 % coolant concentrate. A coolant concentrate level greater than 68 % actually reduces freeze protection in ethylene glycol base coolants. The maximum recommended coolant concentrate level is 60 % which provides freeze protection shown in X1.1.2.

X1.2.15 DO NOT exceed the manufacturer's recommended dosage of SCA or the recommended concentration of coolant

concentrate. Overconcentration can result in plugged radiators, heater cores, and charge air coolers. Overconcentration can also cause water pump seal leaks.

X1.2.16 DO NOT reuse coolant that has been drained from a vehicle in which overconcentration of coolant concentrate or overconcentration of supplemental coolant additives has occurred, in which the coolant is over one year old, or in which the container is dirty.

X1.2.17 DO NOT precharge the cooling system with SCA if the coolant is drained and reused.

X1.2.18 DO NOT use soluble oil additives.

X1.2.19 DO NOT use methyl alcohol or methoxy propanol base coolant concentrates.

X1.2.20 DO NOT use antileak additives if the engine-cooling system is equipped with a coolant filter, as this may plug the filter element. For all other cooling systems, follow the recommendations of the engine or vehicle manufacturer.

X2. CAVITATION CORROSION AND SCALING RESISTANCE TESTING OF SUPPLEMENTAL COOLANT ADDITIVES

X2.1 Cavitation Corrosion Resistance:

X2.1.1 Vehicle and engine manufacturers use a variety of different procedures for determining resistances of engine cylinder liner and engine block material to cavitation corrosion (also referred to as liner pitting). These tests are specific for different manufacturers, and industry has not established a standard accepted procedure or test apparatus. These manufacturers have developed correlations between a given procedure and damage rate for their specific engine designs.

X2.1.2 The most widely used test method is based upon a modification of Test Method G 32, that uses ultrasonic vibratory equipment and a standard size metal specimen for comparing cavitation resistance of either engine materials or engine coolant formulations.

X2.1.3 A vibratory cavitation screening test method for application to engine coolants is currently under development by ASTM Committee D15. Since a standard procedure, recommended equipment, and tolerance ranges have not been established, application of any procedure must be by specific agreement between the coolant concentrate or SCA manufacturer and the user of these products. Such agreements are usually defined by specific purchasing agreements.

X2.2 Hot-Surface Scale Resistance:

X2.2.1 Unstable additives in coolant or SCA concentrate and excessive mineral content in coolant system makeup water tend to deposit on hot engine surfaces. This reduces heat transfer causing engine component overheating.

X2.2.2 Although no standard test has been adopted by ASTM, and deposit limits are therefore undefined, a procedure is under development in ASTM Committee D-15.

X2.2.3 The test under consideration consists of a circulating rig for heating and cooling a test solution and subsequent passing of that solution over a heated element. The element is

weighed before and after a specified operating time to determine the mass increase as a result of deposit buildup.

X2.2.4 Apparatus for this procedure can be procured from several sources. A number of commercial testing laboratories are also equipped to perform testing using this equipment. Further information is available by contacting ASTM Committee D15.

X2.2.5 The use of this test procedure and the establishment of acceptance limits is subject to agreement between the coolant concentrate or SCA concentrate manufacturer and the user of a specific manufacturer's products.

X2.2.6 As an alternative, the producer and user can establish limits of composition for special additives, determined by the manufacturer of the concentrates as effective deposit and scale inhibitors.

X2.2.7 Requirements defined in X2.2.5 or X2.2.6 usually apply to concentrates diluted into a cooling system at the manufacturer's recommended addition levels.

X2.3 Compatibility With Engine Coolants:

X2.3.1 Interference, called incompatibility, between the chemical additives in formulated coolants and a specific SCA product can result in chemical precipitations in the engine-cooling system. The result is sludge that reduces cooling system efficiencies, increases wear and leakage in the water pump, and reduces protection of metal surfaces.

X2.3.2 These conditions can be minimized by following the recommendations of the SCA and the engine or vehicle manufacturer on the correct quantities of SCA for precharging or maintenance application. Do not increase the dosage or frequency of use of SCA products without specific recommendations.

X2.3.3 A test method for compatibility, D 5828, has recently been developed and adopted by ASTM Committee D15.

This test method measures the quantity of precipitates formed upon heating, mixtures of coolant, and SCA products. The greater the quantity of chemical precipitate, the lower is the compatibility of the ingredients. When this test method is standardized and allowable limits are established by ASTM, this test method could become a required part of this SCA specification.

X2.3.4 Producers and users of SCA products can agree to use the tentative procedure described in X2.3.3 or other methods to determine compatibility.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).