



# Standard Test Method for Static Water Absorption of Leather<sup>1</sup>

This standard is issued under the fixed designation D 6015; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method covers the determination of the amount of water absorbed by leather at  $23 \pm 2^\circ\text{C}$  by immersion under static conditions. It may be used on all types of leather. This test method does not apply to wet blue.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:

- D 1517 Terminology Relating to Leather<sup>2</sup>
- D 1610 Practice for Conditioning Leather<sup>2</sup>

## 3. Terminology

3.1 For definitions of leather terms used in this test method refer to Terminology D 1517.

## 4. Summary of Test Method

4.1 In this test method the amount of water absorbed by a leather specimen is measured at room temperature with all surfaces exposed to water.

## 5. Significance and Use

5.1 This test method is used to determine compliance with specifications for water absorption of upper leather. The significance of the test method is limited by the static conditions employed, and the results do not reflect the water absorption under dynamic conditions of flexing.

## 6. Apparatus

- 6.1 *Beaker*, 1000 mL.
- 6.2 *Balance*, sensitive to 0.01 g.
- 6.3 *Blotting Paper*.

## 7. Test Specimen

7.1 The test specimen shall be a square of leather approxi-

mately 4 by 4 in. (102 by 102 mm).

7.2 Unless otherwise specified in the detail specification, one specimen from each test unit of sample shall be tested.

7.3 Prior to testing, the specimen shall be conditioned according to Practice D 1610.

## 8. Procedure

8.1 Weigh the specimen to the nearest 0.01 g and record the mass as  $W_1$ .

8.2 One to three specimens shall be completely immersed in a 1000 mL beaker of distilled water at  $23^\circ\text{C} \pm 2^\circ\text{C}$ . This should be done in such a manner that the surface of the specimens do not touch each other.

8.3 After 1 h  $\pm$  1 min immersion, the specimens shall be removed from the beaker and the surface water from each removed by lightly blotting the specimen with blotting paper prior to weighing.

8.4 The specimen shall then be weighed immediately and the mass recorded as  $W_2$ .

## 9. Calculation

9.1 The amount of water absorbed by each specimen shall be calculated as follows:

$$\text{Water absorbed, \%} = [(W_2 - W_1)/W_1] \times 100 \quad (1)$$

where:

$W_1$  = weight of the original specimen, grams, and

$W_2$  = weight of the specimen after water immersion, grams.

## 10. Report

10.1 The amount of water absorbed by the specimen shall be reported to the nearest 0.01 %.

## 11. Precision and Bias

11.1 This test method is adopted from the procedures of the Federal Government where it has long been in use. It was approved for publication before the inclusion of precision and bias statements was mandated. The original interlaboratory test data is no longer available. The user is cautioned to verify by use of reference materials, if available, that the precision and bias of this test method is adequate for contemplated use.

## 12. Keywords

12.1 leather; static; water absorption

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D31 on Leather and is the direct responsibility of Subcommittee D31.03 on Footwear.

Current edition approved Sept. 10, 2000. Published October 2000. Originally published as D 6015 - 96. Last previous edition D 6015 - 96.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 15.04.

 **D 6015**

*The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)).*