



# Standard Test Method for Measuring Rut-Depth of Pavement Surfaces Using a Straightedge<sup>1</sup>

This standard is issued under the fixed designation E 1703/E 1703M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method describes the procedure for the measurement of the depth of the rut at a chosen location in a pavement surface using a straightedge and a gage.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. Within the text, the inch-pound units are shown in parentheses. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:

E 867 Terminology Relating to Traveled Surface Characteristics<sup>2</sup>

## 3. Terminology

3.1 *Definitions:*—For definitions of terms used in this test method, refer to Terminology E 867.

### 3.2 Definitions of Terms Specific to This Standard:

3.2.1 *rut-depth, n*—the maximum measured perpendicular distance between the bottom surface of the straightedge and the contact area of the gage with the pavement surface at a specific location.

3.2.2 *trueness, n*—the lack of significant curvature, inclination, noteworthy elevations, or depressions.

## 4. Significance and Use

4.1 Rutted pavement surfaces may have an adverse influence on vehicle handling characteristics and may impede surface drainage, which may reduce friction properties and contribute to hydroplaning. Rutting indicates deformation or wear of materials in the pavement and may be indicative of

problems such as asphalt flow, consolidation, shear, or loss of pavement materials.

4.2 The rut-depth value obtained using this test method may not correlate well with values obtained using other methods.

## 5. Apparatus

### 5.1 Straightedge:

5.1.1 *Width*—The bottom rectangular surface of the straightedge shall be at least 19 mm (0.75 in.) but not more than 75 mm (3.0 in.) wide in the measurement plane.

5.1.2 *Length*—The preferred lengths of the straightedge are either 1.83 metres (6 ft), 2 metres (6.56 ft), 3 metres (9.84 ft), 3.05 metres (10 ft), or 3.66 metres (12 ft). The length shall ensure that the straightedge spans the two highest points on either side of the rut. The minimum length shall be at least 1.73 metres (5.67 ft).

5.1.3 *Trueness*—The maximum out-of-trueness of the bottom surface of the straightedge in the measurement plane shall be less than  $\pm 0.40$  mm/m ( $\pm 0.005$  in./ft) of length and less than  $\pm 2.5$  mm/m ( $\pm 0.03$  in./ft) of width. The straightedge must be rigid enough so that it always meets this trueness.

### 5.2 Gage:

5.2.1 The rut-depth measuring gage shall be graduated to 1 mm ( $1/16$  in.) or finer. The bottom surface of the gage shall be at least 19 mm (0.75 in.) but not more than 75 mm (3.0 in.) wide and span areas of aggregate loss and texture. The gage shall have sufficient range to accommodate the measurement.

## 6. Procedure

### 6.1 Straightedge Placement:

6.1.1 Place the straightedge across the rut. Allow the straightedge to rest upon the pavement at two contact areas, such that sliding the straightedge along its length in both directions will not change the contact areas on the pavement. Avoid locating the contact area at discontinuities that are wider than the straightedge bottom.

6.1.2 Place the straightedge in a plane perpendicular to the direction of traffic movement. The bottom surface of the straightedge shall be parallel to the longitudinal slope of the pavement. Do not place the straightedge on any discontinuities on the pavement surface, for example, potholes or loose debris.

6.1.3 The longitudinal interval between successive straightedge placement should be related to the precision required for the use of the data.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee E-17 on Vehicle-Pavement Systems and is the direct responsibility of Subcommittee E17.31 on Methods of Measuring Profile and Roughness.

Current edition approved April 15, 1995. Published June 1995.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 04.03.

6.2 Gage Placement:

6.2.1 Place the gage between the two contact areas perpendicular to the reference plane created by the bottom of the straightedge and perpendicular to the longitudinal slope of the pavement. The bottom of the gage shall be in contact with the pavement at the time of the measurement. Do not place the gage on any discontinuities on the pavement surface, for example, potholes or loose debris (see Fig. 1).

6.3 Rut-Depth Measurement:

6.3.1 Measure the distance between the bottom surface of the straightedge and the pavement after the gage has been

placed as described in 6.1 and 6.2.

6.3.2 Measurements should be made to the nearest graduation of the gage. A sufficient number of measurements should be made along the straightedge to determine the greatest distance between the straightedge and the pavement.

7. Report

7.1 Report at least the following information:

7.1.1 Date,

7.1.2 Test location to uniquely identify the data reported (such as: Road number, Station, Offset, Wheelpath, or Lane),

7.1.3 Dimensions of the bottom surface of the straightedge,

7.1.4 Dimensions of the bottom surface of the gage, and

7.1.5 Greatest rut-depth measurement (see 3.2.2) to the nearest graduation of the gage specified in 5.2.1.

8. Precision and Bias


8.1 At this time no precision estimate from a statistically-designed series of tests at different locations has been obtained.

8.2 Since there is no accepted reference material suitable for determining the bias for the procedure for measuring the rut-depth of pavement surfaces using a straightedge, no statement on bias is being made.

NOTE 1—The precision of each rut-depth measurement depends on the design of the depth gage, surface texture, and operator skill. The precision for the selected equipment should be determined by the user through a statistically-designed series of tests.

9. Keywords

9.1 rut; rut-depth; straightedge; gage



NOTE 1— Fig. 1 represents only one type of rut configuration.

FIG. 1 Rut Configuration

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).