

Methods for

Thermal shock tests on laboratory glassware

Committees responsible for this British Standard

The preparation of this British Standard was entrusted by the Laboratory Apparatus Standards Policy Committee (LBC/-) to Technical Committee LBC/8, upon which the following bodies were represented:

- British Glass Manufacturers' Confederation
- Society of Glass Technology

This British Standard, having been prepared under the direction of the Laboratory Apparatus Standards Policy Committee, was published under the authority of the Standards Board and comes into effect on 29 March 1991

© BSI 10-1999

First published June 1962
Second edition April 1983
Third edition March 1991

The following BSI references relate to the work on this standard:
Committee reference LBC/8
Draft for comment 89/56194 DC

ISBN 0 580 19489 2

Amendments issued since publication

Amd. No.	Date	Comments

Contents

	Page
Committees responsible	Inside front cover
National foreword	ii
1 Scope	1
2 Definitions	1
3 Apparatus	1
4 Sampling	1
5 Procedure	1
6 Expression of results	2
7 Test report	2
Annex A (informative) Bibliography	3
Publication(s) referred to	Inside back cover

National foreword

This British Standard has been prepared under the direction of the Laboratory Apparatus Standards Policy Committee and supersedes BS 3517:1983, which is withdrawn. It is identical with ISO 718:1990 *“Laboratory glassware — Thermal shock and thermal shock endurance — Test methods”* published by the International Organization for Standardization (ISO). It has been prepared by Subcommittee 5, “Quality of glassware”, of Technical Committee 48 “Laboratory glassware and related apparatus”, with the active participation and approval of the UK.

Additional information. Reference is made in clause 1 of the International Standard to ISO 7459 for information only. There is no corresponding British Standard to ISO 7459.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, pages i and ii, pages 1 to 4, an inside back cover and a back cover.

This standard has been updated (see copyright date) and may have had amendments incorporated. This will be indicated in the amendment table on the inside front cover.

1 Scope

This International Standard specifies a thermal shock test and the procedure for determining the thermal shock endurance for laboratory glassware in the condition received by the customer.

This International Standard does not apply to fused silica ware and annealed containers made from soda-lime-silicate glass.

Annealed containers made from soda-lime-silicate glass shall be tested according to ISO 7459.

2 Definitions

For the purposes of this International Standard, the following definitions apply.

2.1

thermal shock

a sudden change in temperature applied to laboratory glassware

2.2

thermal shock endurance Δt_{50}

a temperature difference interpolated by linear regression at which 50 % of the samples will probably fail

2.3

temperature variation

the difference at any moment between the temperature at the centre of the working space and at any other point in the working space of the cold water bath or the test oven

2.4

temperature fluctuation

the short term changes in temperature at any point in the working space of the cold water bath or the test oven

3 Apparatus

3.1 Cold water bath, comprising a bath or tank capable of containing at least five times the total volume of the samples being tested at one time. It shall be fitted with a water circulator, a thermometer and a thermostatic control capable of maintaining the water temperature to within $\pm 1^\circ\text{C}$ of a specified lower temperature, t_2 , within the range 0°C to 27°C .

NOTE 1 The total volume of the samples is taken as the sum of the volume of the individual samples when each is regarded as being solid.

3.2 Test oven, preferably electrically heated with a temperature range up to at least 300°C . It shall be fitted with an air circulating device to ensure that the temperature variation does not exceed $\pm 5^\circ\text{C}$ and a thermostatic control capable of maintaining the test oven temperature fluctuation within $\pm 1^\circ\text{C}$ up to 180°C and within $\pm 2^\circ\text{C}$ between 180°C and 300°C .

3.3 Tongs, with tips protected by a heat resisting material such as glass or mineral wool.

3.4 Gloves, gauntlet-type and preferably made from an asbestos-substitute material.

3.5 Basket, for testing two or more samples simultaneously. It shall be made out of or coated with a material which will not scratch or scuff the samples during the test procedure. It shall be capable of holding the samples upright and separate and of allowing a free passage of water and air between them. It shall prevent the sample from floating when immersed. For the multiple testing of samples, it may be combined with an automatic device for placing the basket of samples in the test oven (3.2) and transferring it to the cold water bath (3.1).

4 Sampling

The test shall be performed on a predetermined number of articles.

The number of articles to be taken as samples from a consignment should be specified in the appropriate standard for the type of article to be tested. In default of this the number should be agreed between the interested parties.

The articles used for the test shall not have been subjected to any other mechanical or thermal test procedure which could adversely affect their thermal shock endurance.

The samples shall be selected to provide the information which is required from the particular test. If the selecting procedure is not specified, the samples shall be taken at random.

5 Procedure

5.1 Remove any dirt or loose debris from the samples and dry them if necessary.

5.2 Place the samples, either separately or contained in the basket (3.5), in the test oven (3.2) which has been previously heated to the upper temperature, t_1 . Maintain the samples at that temperature for a period of time sufficient to ensure that the glass has reached temperature equilibrium; 30 min is normally sufficient.

NOTE 2 The time required to reach temperature equilibrium depends on the maximum glass thickness and experience has shown that at least 6 min/mm is needed.

Place the cold water bath (3.1) near the test oven and achieve and maintain it at the specified lower temperature, t_2 , within the range 0 °C to 27 °C.

5.3 Then remove the samples from the test oven (3.2) either one at a time, holding them with the tongs (3.3) or gloves (3.4) if the samples are large, or contained in the basket (3.5). Immerse the samples which are not containers as completely as possible in the cold water bath (3.1), for a specified period of at least 8 s but not more than 2 min. Keep the tips of the tongs or the fingers of the gloves dry. Do not handle hot glassware with wet tips or gloves. Immerse containers to half the total height less the neck if any.

When the rims of the articles are to be tested, immerse the samples vertically, rim first, to a depth of about 25 mm and take care that entrapped air does not escape.

The process of transferring the samples, timed from opening the test oven to the immersion, shall be completed in $5\text{ s} \pm 1\text{ s}$ for each sample or for the basket containing the samples. The difference in temperature between the test oven and the cold water bath shall not be more than $\pm 3\text{ °C}$ from the required value at the time of transference.

5.4 Then remove the samples from the cold water bath and evaluate them immediately according to 6.1.

5.5 For determining the thermal shock endurance, repeat the testing according to 5.2 to 5.4 with increasing temperature difference values, $t_1 - t_2$, until all of the samples have failed. The increments of temperature t_1 , shall be 5 °C for $t_1 - t_2 \leq 100\text{ °C}$ and 10 °C for $t_1 - t_2 > 100\text{ °C}$.

6 Expression of results

6.1 Samples which do not chip, crack or break after removal from the cold water bath (3.1) are considered to have passed the thermal shock test at the temperature difference of $t_1 - t_2$.

6.2 For the thermal shock endurance, record the number of failures at each temperature difference and determine the Δt_{50} value and the standard deviation s from a graph of the cumulative percentage of failures against the temperature difference at which the samples failed.

7 Test report

The test report shall include:

- a) a reference to this International Standard;
- b) an identification of the article tested (e.g. shape, volume, mass, description, glass colour, surface condition);
- c) the number of articles in the consignment;
- d) the number of samples taken for the test and sampling method;
- e) for the thermal shock test:
 - the temperature difference $t_1 - t_2$ in degrees Celsius,
 - the number of samples which passed the test;
- f) for the thermal shock endurance test:
 - the temperature difference Δt_{50} at which 50 % of the samples will probably fail;
 - the standard deviation s .

Annex A (informative)

Bibliography

[1] ISO 7459:1984, *Glass containers — Thermal shock resistance and thermal shock endurance — Test methods*.

Publication(s) referred to

See national foreword.

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: 020 8996 9000. Fax: 020 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: 020 8996 9001. Fax: 020 8996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: 020 8996 7111. Fax: 020 8996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: 020 8996 7002. Fax: 020 8996 7001.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager. Tel: 020 8996 7070.