

CONFIRMED  
JUNE 1986

*[Falling ball impact]  
Incorporating  
Amendment Nos. 1  
and 2*

# Methods of Test for Paints —

## Part E7: Resistance to impact (falling ball test)

It is recommended that this Part be read in conjunction with the general information in the Introduction to BS 3900 issued separately (revised edition published March 1969)

UDC 667.61 + 667.613:620.178.7

Confirmed  
October 2008

# Foreword

NOTE This Part describes a procedure based on DEF/1053 “Standard methods of testing paint, varnish, lacquer and related products”, Method No. 17(c) “Resistance to impact — Falling ball”.

Other related Parts of BS 3900 are:

- *Part E3: “Impact (falling weight) resistance”, which describes a method where the depth of indentation of the test panel is controlled, whereas in this Part (E7) there is no control of the depth of indentation;*
- *Part E8: “Resistance to impact (pendulum test)”, which describes a method in which resistance to a single-blow impact by a pendulum is determined.*

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

**Compliance with a British Standard does not of itself confer immunity from legal obligations.**

## Summary of pages

This document comprises a front cover, an inside front cover, pages i and ii, pages 1 and 2 and a back cover.

This standard has been updated (see copyright date) and may have had amendments incorporated. This will be indicated in the amendment table on the inside front cover.

## Amendments issued since publication

Amd. No.	Date of issue	Comments
2518	April 1978	
6909	February 1992	Indicated by a sideline in the margin

# Content

	Page
Foreword	Inside front cover
1 Scope	1
2 Supplementary information	1
3 Apparatus	1
4 Sampling	1
5 Test panel	1
6 Procedure	1
7 Test report	2



## 1 Scope

This Part describes a procedure for determining the resistance to impact of a single-coat film or a multicoat system of paints, varnishes, or related products, using a free falling ball.

The method is specifically intended to test products on substrates which are not significantly distorted in the test.

## 2 Supplementary information

The method of test described below requires to be completed, for any particular application, by the following supplementary information. This information is to be derived from the British Standard or other specification for the product under test or, where appropriate, is to be the subject of agreement between the interested parties.

- 1) Material and surface preparation of substrate.
- 2) Method of application of test coating to substrate.
- 3) Thickness, in micrometres, of dry coating, including method of measurement in accordance with BS 3900-C5<sup>1)</sup>, and whether it is a single-coat film or a multicoat system.
- 4) Duration and conditions of drying of the coated panel (or conditions of stoving and ageing, if applicable) before testing.
- 5) Whether the test is to be carried out with the test coating facing upwards or downwards.
- 6) The test requirements the material has to meet.

## 3 Apparatus

**3.1 Hardened steel ball**, approximately 60 mm in diameter and of mass  $900 \pm 10$  g, unless otherwise specified.

**3.2 Device**, e.g. an electromagnet for holding and releasing the steel ball at a specified height above the test panel.

**3.3 Supporting frame**, on which the test panel rests in a horizontal position so as to leave an area  $180 \text{ mm} \times 180 \text{ mm}$  unsupported.

## 4 Sampling

A representative sample of the product to be tested (or of each product in the case of a multicoat system) shall be taken as described in BS 3900-A1<sup>2)</sup>. The sample(s) shall then be examined and prepared for testing as described in BS 3900-A2<sup>3)</sup>.

## 5 Test panel

**5.1 Material and dimensions.** Unless otherwise specified or agreed, the test panel shall be of burnished steel, approximately  $200 \text{ mm} \times 200 \text{ mm}$  and at least 5 mm thick, complying with the requirements of BS 1449-1<sup>4)</sup>, HRP 43/25.

**5.2 Preparation and coating of panel.** Unless otherwise specified, the test panel shall be prepared as described in BS 3900-A3<sup>5)</sup> and shall then be coated with the product or system under test by a method agreed between the interested parties (see clause 2).

**5.3 Drying the test panel.** The coated test panel shall be dried (or stoved and aged) for the specified time and under the specified conditions and, unless otherwise specified, shall be conditioned at a temperature of  $23 \pm 2$  °C and a relative humidity of  $50 \pm 5$  % for a minimum of 16 h. The test procedure shall then be carried out as soon as possible.

**5.4 Thickness of coating.** The thickness, in micrometres, of the dry coating shall be determined by the method specified, using one of the procedures in BS 3900-C5<sup>6)</sup>.

## 6 Procedure

**6.1** Place the panel on the supporting frame with the test coating facing upward or downwards as specified. Release the steel ball and allow it to fall freely from a height of 3 m, unless otherwise specified, so that it strikes the panel approximately in the centre. Repeat this procedure so that the second point of impact is as close to the first as possible and, in any case, is not more than 20 mm from it.

**6.2** Remove the panel from the supporting frame and examine the coating for signs of cracking, flaking and detachment from the substrate.

<sup>1)</sup> BS 3900-C5 "Determination of film thickness"

<sup>2)</sup> BS 3900-A1 "Sampling".

<sup>3)</sup> BS 3900-A2 "Examination and preparation of samples for testing".

<sup>4)</sup> BS 1449, "Steel plate, sheet and strip", Part 1 "Carbon steel plate, sheet and strip".

<sup>5)</sup> BS 3900-A3 "Standard panels for paint testing".

<sup>6)</sup> BS 3900-C5 "Determination of film thickness".

## 7 Test report

The test report shall contain at least the following information:

- 1) A reference to this British Standard.
- 2) Type and identification of the coating under test.
- 3) The items of supplementary information referred to in Clause 2.
- 4) The British Standard or other document supplying the information referred to in Clause 7 3) above.
- 5) Any deviation, by agreement or otherwise, from the standard test procedure described.
- 6) The results of the test in terms of the stated requirements.
- 7) Date of the test.



---

# **BSI — British Standards Institution**

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

## **Revisions**

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: 020 8996 9000. Fax: 020 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

## **Buying standards**

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: 020 8996 9001. Fax: 020 8996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

## **Information on standards**

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: 020 8996 7111. Fax: 020 8996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: 020 8996 7002. Fax: 020 8996 7001.

## **Copyright**

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager. Tel: 020 8996 7070.