

Methods of test for

# aluminium oxide —

## Part 14: Determination of calcium content

ICS 71.100.10

# National foreword

This British Standard reproduces verbatim ISO 2070:1997 and implements it as the UK national standard. It supersedes BS 4140-14:1990 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee CII/24, Raw materials for the aluminium industry, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

### Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the BSI Standards Catalogue under the section entitled “International Standards Correspondence Index”, or by using the “Find” facility of the BSI Standards Electronic Catalogue.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

**Compliance with a British Standard does not of itself confer immunity from legal obligations.**

### Summary of pages

This document comprises a front cover, an inside front cover, pages i and ii, the ISO title page, pages ii to iv, pages 1 to 3 and a back cover.

This standard has been updated (see copyright date) and may have had amendments incorporated. This will be indicated in the amendment table on the inside front cover.

### Amendments issued since publication

Amd. No.	Date	Comments

This British Standard, having been prepared under the direction of the Sector Board for Materials and Chemicals, was published under the authority of the Standards Board and comes into effect on 15 August 1997

© BSI 09-1999

ISBN 0 580 27540 X

# Contents

	Page
National foreword	Inside front cover
Foreword	iii
Text of ISO 2070	1



# INTERNATIONAL STANDARD

**ISO  
2070**

Second edition  
1997-03-01

---

---

## **Aluminium oxide primarily used for the production of aluminium — Determination of calcium content**

*Oxyde d'aluminium principalement utilisé pour la production de  
l'aluminium —  
Dosage du calcium*



Reference number  
ISO 2070:1997(E)

Contents

	Page
Foreword	iii
1 Scope	1
2 Normative references	1
3 Principle	1
4 Reagents	1
5 Apparatus	1
6 Preparation of test sample	2
7 Procedure	2
8 Expression of results	2
9 Precision	2
10 Test report	3
Table 1 — Calibration solutions	2

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 2070 was prepared by the British Standards Institution (BSI) (as BS 4140-14:1990) and was adopted under a special “fast-track procedure”, by Technical Committee ISO/TC 47, *Chemistry*, in parallel with its approval by the ISO member bodies.

It cancels and replaces ISO 2070:1981 of which it constitutes a technical revision.

**Descriptors:** Aluminium oxide, chemical analysis, determination of content, calcium, flame photometric analysis, atomic absorption spectrometric method, extractive metallurgy.





## 1 Scope

This International Standard describes a flame atomic absorption method for the determination of the calcium content of aluminium oxide primarily used for the production of aluminium.

The method is applicable to products having a calcium content, expressed as CaO, of not less than 0,002 % (m/m).

## 2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 648:1977, *Laboratory glassware — One-mark pipettes*.

ISO 802:1976, *Aluminium oxide primarily used for the production of aluminium — Preparation and storage of test samples*.

ISO 1042:1983, *Laboratory glassware — One-mark volumetric flasks*.

ISO 2073:1976, *Aluminium oxide primarily used for the production of aluminium — Preparation of solution for analysis — Method by hydrochloric acid attack under pressure*.

ISO 3696:1987, *Water for analytical laboratory use — Specification and test methods*.

## 3 Principle

A test portion is dissolved in hydrochloric acid under pressure.

The solution is aspirated into a dinitrogen oxide (nitrous oxide) acetylene flame and the calcium content determined by spectrometric measurement of the absorption at a wavelength of 422,7 nm using a calcium hollow-cathode lamp.

## 4 Reagents

Except where otherwise stated, use only reagents of recognized analytical grade and water complying with grade 2 of ISO 3696. Do not use leaded-glass reagent vessels.

**4.1 Aluminium oxide**, of purity greater than 99,95 %, containing less than 0,000 1 % (m/m) of CaO.

**4.2 Hydrochloric acid solution**,  $\rho \approx 1,19$  g/ml, about 38 % (m/m).

**4.3 Aluminium, acid solution**, having an aluminium concentration equivalent to that of a 20 g/l solution of alumina ( $\text{Al}_2\text{O}_3$ ).

Wash approximately 11 g of extra-pure aluminium shavings [99,999 % (m/m)], in 2 ml to 3 ml of nitric acid solution [ $\rho \approx 1,4$  g/ml, about 68 % (m/m)]. Rinse the shavings with water, wash them with acetone in a fume cupboard and blow or suck dry.

Weigh, to the nearest 1 mg, 10,585 g of the dried shavings, place them in a beaker of suitable capacity (for example 500 ml and add 144 ml of hydrochloric acid solution (4.2). Add 1 drop of extra-pure mercury to aid the attack. Wait until the reaction subsides and maintain a gentle heat until all the aluminium has dissolved. Allow to cool, transfer the solution quantitatively to a 500 ml one-mark volumetric flask (5.2), dilute to the mark and mix.

**4.4 Standard calcium solution**,  $c(\text{CaO}) = 0,020$  g/l.

Heat about 1 g of calcium carbonate in an oven at  $110^\circ\text{C} \pm 5^\circ\text{C}$  for 16 h and cool in a desiccator. Weigh, to the nearest 0,000 1 g, 0,178 5 g of the calcium carbonate and transfer to a beaker of suitable capacity (for example 100 ml) and dissolve in 5,5 ml of hydrochloric acid solution (4.2). Transfer the solution quantitatively to a 1 000 ml one-mark volumetric flask (5.2), dilute to the mark and mix.

Transfer, by pipette, 100 ml of this solution to a 500 ml one-mark volumetric flask (5.2), dilute to the mark and mix.

**4.5 Strontium chloride solution**,  $c(\text{SrCl}_2) = 100$  g/l.

Weigh, to the nearest 1 mg, 25,000 g of strontium chloride of calcium content less than 0,001 % (m/m) and transfer to a beaker of suitable capacity (for example 250 ml) and dissolve in about 100 ml of water. Transfer the solution quantitatively to a 250 ml one-mark volumetric flask (5.2), dilute to the mark and mix.

## 5 Apparatus

Only borosilicate glassware or plastics materials shall be used. Only ground-glass or plastic stoppers shall be used, and not rubber.

Ordinary laboratory apparatus, the apparatus described in 3.3.2 of ISO 802:1976, in clause 5 of ISO 2073:1976 and the following are required.

**5.1 One-mark pipettes**, complying with ISO 648, class A.

**5.2 One-mark volumetric flasks**, complying with ISO 1042, class A.

**5.3 Spectrometer**, atomic absorption type, fitted with a burner fed from cylinders of acetylene and dinitrogen oxide (nitrous oxide), and with a calcium hollow-cathode lamp.

6 Preparation of test sample

Prepare a test sample in accordance with ISO 802.

7 Procedure

7.1 Test portion

Weigh, to the nearest 1 mg, 2 g of the test sample prepared in clause 6.

7.2 Determination

7.2.1 Preparation of test solution

Take the test portion prepared in 7.1 and follow the procedure described in ISO 2073. Transfer the resulting solution quantitatively to a 100 ml one-mark volumetric flask. Add, using a pipette (5.1), 5 ml of strontium chloride solution (4.5), dilute to the mark and mix.

7.2.2 Preparation of blank test solution

Follow the procedure described in 7.2.1 but replace the test portion with the same mass of aluminium oxide (4.1), weighed to the nearest 1 mg.

7.2.3 Preparation of calibration solutions

Into each of a numbered series of six 100 ml one-mark volumetric flasks (5.2), transfer, using a 50 ml pipette (5.1), 50 ml of the acid solution of aluminium (4.3) followed by the corresponding portions of the calcium solution (4.4) shown in Table 1, using pipettes (5.1). Add, using a pipette (5.1), 5 ml of strontium chloride solution (4.5), dilute to the mark and mix.

7.2.4 Adjustment and operation of the spectrometer

Operate the spectrometer (5.3) throughout the determination in accordance with the manufacturer's instructions. Adjust the wavelength to 422,7 nm and alter the sensitivity and the aperture of the slit according to the characteristics of the instrument. Adjust the pressure of the dinitrogen oxide (nitrous oxide) and acetylene according to the characteristics of the burner, to obtain an oxidizing flame.

7.2.5 Spectrometric measurements

Carry out measurements at regular intervals in a random order of the test solution (see 7.2.1), the blank test solution (see 7.2.2) and the calibration solutions (see 7.2.3), taking care to maintain a constant aspiration rate. Take repeat readings of all solutions in the reverse order to compensate for drift, and calculate the mean of the duplicate absorbance values.

Table 1 — Calibration solutions

No.	Volume of calcium solution ml	Corresponding mass of calcium oxide mg
1 <sup>a</sup>	0	0
2	5	0,10
3	10	0,20
4	15	0,30
5	20	0,40
6	25	0,50

<sup>a</sup> Calibration blank solution.

8 Expression of results

8.1 Calibration curve

Correct each measurement obtained in 7.2.5 by subtracting the value given by the blank calibration solution numbered “1”. Prepare a calibration curve by plotting corrected absorbance against the corresponding mass, in milligrams, of CaO.

Determine the quantities, in milligrams, of CaO corresponding to the absorbance measurements for the test solution and the blank test solution.

8.2 Calculation

The calcium content *w*, expressed as a percentage by mass of calcium oxide (CaO), is given by the following equation:

$$w = \frac{(m_0 - m_1)}{1\,000} \times \frac{100}{2}$$

where

- m*<sub>0</sub> is the mass, in milligrams, of calcium oxide found in the test solution;
- m*<sub>1</sub> is the mass, in milligrams, of calcium oxide found in the blank test solution.

Express the result to three decimal places.

9 Precision

The precision of this method is not known because interlaboratory data are not available. Interlaboratory data are being obtained, and a precision statement will be added at the next revision.

## 10 Test report

The test report shall include the following information:

- a) a complete identification of the sample;
- b) reference to this International Standard, i.e. ISO 2070:1997;
- c) the results, expressed in accordance with clause 8;
- d) details of any unusual features noted during the determination;
- e) details of any operation not included in this International Standard or in the International Standard to which reference is made, as well as any operation regarded as optional.

---

# BSI — British Standards Institution

---

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

## Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: 020 8996 9000. Fax: 020 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

## Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: 020 8996 9001. Fax: 020 8996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

## Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: 020 8996 7111. Fax: 020 8996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: 020 8996 7002. Fax: 020 8996 7001.

## Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager. Tel: 020 8996 7070.