

Methods of test for Aluminium oxide —

Part 17: Determination of fluorine content

[ISO title: Aluminium oxide primarily used for the production of aluminium — Determination of fluorine content — Alizarin complexone and lanthanum chloride spectrophotometric method]

NOTE It is recommended that this Part be read in conjunction with the general information given in BS 4140-0 “*General introduction*” which is issued separately.

UDC 661.862.22:546.16:543.42

This British Standard, having been prepared under the direction of the Chemicals Standards Committee, was published under the authority of the Executive Board and comes into effect on 28 February 1986

© BSI 11-1999

The following BSI references relate to the work on this standard:
Committee reference CIC/24
Draft for comment 85/52366 DC

ISBN 0 580 14994 3

Amendments issued since publication

Amd. No.	Date of issue	Comments

Contents

	Page
National foreword	ii
1 Scope and field of application	1
2 References	1
3 Principle	1
4 Reagents	1
5 Apparatus	2
6 Procedure	2
7 Expression of results	3
8 Test report	3
Publications referred to	Inside back cover

National foreword

This Part of BS 4140 is identical with ISO 2828:1973 “*Aluminium oxide primarily used for the production of aluminium — Determination of fluorine content — Alizarin complexone and lanthanum chloride spectrophotometric method*”, published by the International Organization for Standardization (ISO).

The method supersedes clause 17 of Addendum No. 3 (1974) to BS 4140:1967. Parts 17 to 19 of this standard collectively supersede Addendum No. 3 (1974) to BS 4140:1967 which is withdrawn.

Terminology and conventions. The text of the International Standard has been approved as suitable for publication as a British Standard without deviation.

Some terminology and certain conventions are not identical with those used in British Standards; attention is drawn especially to the following.

The comma has been used as a decimal marker. In British Standards it is current practice to use a full point on the baseline as the decimal marker.

In British Standards it is current practice to use the symbol “L” for litre (and its submultiples) rather than “l”.

Wherever the words “International Standard” appear, referring to this standard, they should be read as “British Standard”.

Cross-references

International Standard	Corresponding British Standard
ISO/R 802:1968 (Revised as ISO 802:1976)	BS 4140 <i>Methods of test for aluminium oxide</i> Part 1:1986 <i>Preparation and storage of test samples</i> (Identical)
ISO/R 2073:1971 (Revised as ISO 2073:1976)	Part 13:1986 <i>Preparation of sample solution by treatment with hydrochloric acid under pressure</i> (Identical)

ISO/R 1693:1970, which is referred to in the text, has been revised as ISO 1693:1976. The Technical Committee has reviewed the provisions of ISO 1693:1976 and has decided that they are acceptable for use in conjunction with this standard. Clause 4 of BS 5050:1974 is related to ISO 1693:1976.

This standard prescribes methods of test only, and should not be used or quoted as a specification defining limits of purity. Reference to this Part should indicate that the method of test used complies With BS 4140-17:1986.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, pages i and ii, pages 1 to 4, an inside back cover and a back cover.

This standard has been updated (see copyright date) and may have had amendments incorporated. This will be indicated in the amendment table on the inside front cover.

1 Scope and field of application

This International Standard specifies a spectrophotometric method, using alizarin complexone and lanthanum chloride, for the determination of the fluorine content of aluminium oxide primarily used for the production of aluminium.

The method is applicable to fluorine (F) contents greater than 0,003 %.

2 References

ISO/R 802, *Aluminium oxide primarily used for the production of aluminium — Preparation and storage of test samples.*

ISO/R 1693, *Cryolite (natural and artificial) — Determination of fluorine content — Modified Willard-Winter method.*

ISO/R 2073, *Aluminium oxide primarily used for the production of aluminium — Preparation of sample solution for analysis by means of attack by hydrochloric acid under pressure.*

3 Principle

Dissolution of a test portion by attack by sulphuric acid under pressure.

Separation of the fluorine by distillation. Formation of a blue-coloured complex between the fluorine and the combined alizarin complexone/lanthanum chloride reagent at a pH between 4,5 and 4,6. Addition of acetone to increase the stability and sensitivity of the fluorine complex.

Spectrophotometric measurement of the complex at a wavelength of about 620 nm.

4 Reagents

Distilled water, or water of equivalent purity, shall be used in the test.

4.1 Sulphuric acid, approximately 17,5 N solution.

Carefully add, in small portions, 50 ml of sulphuric acid, ρ approximately 1,84 g/ml, about 96 % (m/m) solution, to about 50 ml of water and, after cooling, dilute to 100 ml.

4.2 Sulphuric acid, approximately 24 N solution.

Carefully add, in small portions, 200 ml of sulphuric acid, ρ approximately 1,84 g/ml, about 96 % (m/m) solution, to 100 ml of water and, after cooling, dilute to 300 ml.

4.3 Combined reagent

To prepare this reagent mix, in order, the solutions 4.3.1, 4.3.2 and 4.3.3, add 250 ml of the acetone (4.4) and then dilute to 1 000 ml.

4.3.1 Alizarin complexone solution

Dissolve 0,154 g of alizarin complexone (1,2-dihydroxy-anthraquino-3-yl methylamine-*NN*-diacetic acid) in about 100 ml of water to which has been added 1 ml of ammonia solution (ρ approximately 0,91 g/ml, about 24 % (m/m) solution). After dissolution, add 1 ml of glacial acetic acid (ρ approximately 1,05 g/ml, about 17,4 N solution).

4.3.2 Buffer solution

Dissolve 34 g of sodium acetate trihydrate ($\text{CH}_3\text{COONa} \cdot 3\text{H}_2\text{O}$) and 15 ml of glacial acetic acid (ρ approximately 1,05 g/ml, about 17,4 N solution), in about 150 ml of water.

4.3.3 Lanthanum chloride solution

Dissolve 0,372 g of lanthanum chloride heptahydrate ($\text{LaCl}_3 \cdot 7\text{H}_2\text{O}$) in about 100 ml of water.

NOTE After mixing the solutions, allow to stand for at least 24 h and, preferably, 2 to 3 days before use. The mixed solution is stable for about 2 weeks. The pH is between 4,55 and 4,60.

4.4 Acetone, ρ approximately 0,80 g/ml.

4.5 Fluorine, standard solution corresponding to 0,200 g of fluorine (F) per litre.

Weigh, to the nearest 0,000 1 g, 0,442 0 g of extra pure anhydrous sodium fluoride (NaF) previously heated to 600 °C in a platinum crucible and allowed to cool in a desiccator. Transfer to a beaker of suitable capacity (for example, 100 ml) and dissolve in water. Transfer the solution quantitatively to a 1 000 ml one-mark volumetric flask, dilute to the mark and mix.

1 ml of this standard solution contains 0,200 mg of F.

Store the solution in a plastics flask.

NOTE If extra pure sodium fluoride is not available, recrystallize the product. Dissolve about 5 g of pure sodium fluoride in 125 ml of water and, after dissolution, filter under vacuum through a small Buchner funnel. Then evaporate the solution, in a platinum dish, down to approximately 60 ml. Cool to about 50 °C and separate the sodium fluoride crystals by centrifuging. Wash the crystals three times, always by centrifuging, with small quantities of cold water.

Transfer the product to a platinum dish and dry in an electric oven, with natural draught, at 110 ± 2 °C.

Remove the dish from the oven, cool in a desiccator, grind the product in an agate mortar, and then pass it through a sieve with a mesh size of 355 μm (see ISO/R 565). Put the sieved sodium fluoride in a platinum dish, heat for 2 h at 600 °C, and allow to cool in a desiccator.

4.6 Fluorine, standard solution corresponding to 0,010 g of fluorine (F) per litre.

Transfer 50,0 ml of the standard solution (4.5) to a 1 000 ml one-mark volumetric flask, dilute to the mark and mix.

1 ml of this standard solution contains 10 μg of F. Prepare this solution immediately before use.

4.7 Fluorine, standard solution corresponding to 0,002 0 g of fluorine (F) per litre.

Transfer 50,0 ml of the standard solution (4.6) to a 250 ml one-mark volumetric flask, dilute to the mark and mix.

1 ml of this standard solution contains 2 µg of F.

Prepare this solution immediately before use.

5 Apparatus

Ordinary laboratory apparatus, and

5.1 Apparatus specified in ISO/R 2073

5.2 Apparatus for the steam distillation of fluorine, as specified in 5.3, 5.4 and 5.5 of ISO/R 1693.

5.3 Burette, graduated in 0,05 ml divisions (see ISO/R 385).

5.4 Spectrophotometer

6 Procedure

6.1 Test portion

Weigh, to the nearest 0,001 g, about 1 g of the laboratory sample, dried at 300 °C, prepared as described in 2.3 of ISO/R 802.

The mass of test portion should be reduced to 0,5 g if the expected fluorine content is higher than 0,1 %.

6.2 Blank test

Carry out a blank test at the same time as the determination following the same procedure and using the same quantities of all the reagents used in the test, but omitting the pure aluminium oxide.

6.3 Preparation of the calibration curve

6.3.1 Preparation of standard colorimetric solutions, corresponding to measurements carried out with an optical path length of 1 cm.

Into a series of nine 100 ml one-mark volumetric flasks, place the volumes of the standard fluorine solution (4.7) indicated in the following table.

Standard fluorine solution (4.7)	Corresponding mass of fluorine
ml	µg
0 ^a	0
1,0	2
2,0	4
4,0	8
5,0	10
10,0	20
15,0	30
20,0	40
30,0	60

^a Compensation solution.

Add to each flask 20 ml of the acetone (4.4) and 40 ml of the combined reagent (4.3).

Check that the pH of each solution is between 4,5 and 4,6, adjusting if necessary by the addition of glacial acetic acid or a 500 g/l ammonium acetate solution.

Dilute the contents of each flask to the mark and mix.

Allow the flasks to stand for 1 h protected from light.

6.3.2 Spectrophotometric measurements

After 1 h, carry out the spectrophotometric measurements using the spectrophotometer (5.4) at a wavelength of about 620 nm, after having adjusted the instrument to zero absorbance against the compensation solution.

6.3.3 Preparation of the calibration chart

Plot a graph having, for example, the numbers of milligrams of fluorine contained in 100 ml of the standard colorimetric solutions as abscissae and the corresponding values of the absorbance as ordinates.

6.4 Determination

6.4.1 Preparation of the test solution

Prepare the test solution using the apparatus specified in 5.1, following the technique in a sealed tube described in ISO/R 2073, substituting, in all cases, 5,5 ml of the sulphuric acid solution (4.1) and 5 ml of water for the specified quantities of hydrochloric acid and water.

If the mass of the test portion is 0,5 g, however, the volumes of sulphuric acid solution (4.1) and water shall be 3 ml and 2,5 ml respectively.

6.4.2 Distillation

Place the test solution (6.4.1) in the distillation flask of the apparatus (5.2). Then carry out the distillation procedure by the method described in 6.3.2 of ISO/R 1693, but with the following details:

- distillation with sulphuric acid: use 65 ml of the sulphuric acid solution (4.2);
- temperature of distillation: 150 ± 1 °C.

6.4.3 Colour development

Take an aliquot portion of the distillate containing between 2 µg and 60 µg of fluorine, of which the volume shall not exceed 30 ml, and transfer it to a 100 ml one-mark volumetric flask. Add 20 ml of the acetone (4.4) and 40 ml of the combined reagent (4.3).

Check that the pH is between 4,5 and 4,6, adjusting, if necessary, by the addition of glacial acetic acid or a 500 g/l ammonium acetate solution.

Dilute to the mark and mix.

Allow to stand for 1 h protected from light.

6.4.4 Spectrophotometric measurement

After 1 h, carry out the spectrophotometric measurement using the spectrophotometer (5.4) at a wavelength of about 620 nm, after having adjusted the instrument to zero absorbance against the blank test solution (6.2).

7 Expression of results

By means of the calibration chart (6.3.3), determine the quantity of fluorine corresponding to the value of the absorbance.

The fluorine content, expressed as a percentage by mass of fluorine (F), is given by the formula:

$$m_1 \times \frac{D}{10 \times m_0}$$

where

m_0 is the mass, in grams, of the test portion;

m_1 is the mass, in milligrams, of fluorine found in the aliquot portion of the test solution;

D is the ratio between the volume of the distillate and the volume of the aliquot portion taken for the colour development.

8 Test report

The test report shall include the following particulars:

- a) the reference of the method used;
- b) the results and the method of expression used;
- c) any unusual features noted during the determination;
- d) any operation not included in this International Standard or those documents to which reference is made, or regarded as optional.

Publications referred to

See national foreword.

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: 020 8996 9000. Fax: 020 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: 020 8996 9001. Fax: 020 8996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: 020 8996 7111. Fax: 020 8996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: 020 8996 7002. Fax: 020 8996 7001.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager. Tel: 020 8996 7070.