



Standard Specification for Nickel-Chromium-Iron-Molybdenum-Copper Alloy Rod¹

This standard is issued under the fixed designation B 581; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification² covers rod of Ni-Cr-Fe-Mo-Cu alloys (UNS N06007, N06975, N06985, N06030, and N08031)* as shown in Tables 1-3, for use in general corrosive service.

1.2 The following products are covered under this specification:

1.2.1 Rods $\frac{5}{16}$ to $\frac{3}{4}$ in. (7.94 to 19.05 mm) excl in diameter, hot- or cold-finished, solution annealed and pickled or mechanically descaled.

1.2.2 Rods $\frac{3}{4}$ to $3\frac{1}{2}$ in. (19.05 to 88.9 mm) incl in diameter, hot- or cold-finished, solution annealed, ground or turned.

1.3 The values stated in inch-pound units are to be regarded as the standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet for this product/material as provided by the manufacturer, to establish appropriate safety and health practices, and determine the applicability of regulatory limitations.*

2. Referenced Documents

2.1 ASTM Standards:

B 880 Specification for General Requirements for Chemical Check Analysis Limits for Nickel, Nickel Alloys and Cobalt Alloys³

E 8 Test Methods for Tension Testing of Metallic Materials⁴

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications⁵

E 55 Practice for Sampling Wrought Nonferrous Metals and

Alloys for Determination of Chemical Composition⁶
E 1473 Test Methods for Chemical Analysis of Nickel, Cobalt, and High-Temperature Alloys⁶

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *rod*—material of round solid section furnished in straight lengths.

4. Ordering Information

4.1 It is the responsibility of the purchaser to specify all requirements that are necessary for material ordered under this specification. Examples of such requirements include, but are not limited to the following:

4.1.1 *Alloy*—Table 1.

4.1.2 *Dimensions*—Nominal diameter and length. The shortest useable multiple length shall be specified (Table 4).

4.1.3 *Certification*—State if certification or a report of test results is required (Section 16).

4.1.4 *Purchaser Inspection*—State which tests or inspections are to be witnessed (Section 14).

4.1.5 *Samples for Product (Check) Analysis*—State whether samples shall be furnished (10.2.2).

5. Chemical Composition

5.1 *Heat Analysis*—The material shall conform to the composition limits specified in Table 1.

5.2 *Product (Check) Analysis*—If a product (check) analysis is made by the purchaser, the material shall conform to the requirements specified in Table 1 subject to the permissible tolerances in Specification B 880.

6. Mechanical and Other Requirements

6.1 The material shall conform to the requirements of Table 2.

7. Straightness

7.1 The maximum curvature (depth of cord) shall not exceed 0.050 in. multiplied by the length in feet (0.04 mm multiplied by the length in centimetres).

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved Oct. 10, 2002. Published December 2002. Originally approved in 1973. Last previous edition approved in 1997 as B 581 – 97.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SB-581 in Section II of that Code.

* New designation established in accordance with ASTM E 527 and SAE J1086, Practice for Numbering Metals and Alloys (UNS).

³ *Annual Book of ASTM Standards*, Vol 02.04.

⁴ *Annual Book of ASTM Standards*, Vol 03.01.

⁵ *Annual Book of ASTM Standards*, Vol 14.02.

⁶ *Annual Book of ASTM Standards*, Vol 03.05.



TABLE 1 Chemical Requirements

Element	Composition Limits, %				
	Alloy N06007	Alloy N06975	Alloy N06985	Alloy N06030	Alloy N08031
Nickel	remainder ^A	47.0–52.0	remainder ^A	remainder ^A	30.0–32.0
Chromium	21.0–23.5	23.0–26.0	21.0–23.5	28.0–31.5	26.0–28.0
Iron	18.0–21.0	remainder ^A	18.0–21.0	13.0–17.0	remainder ^A
Molybdenum	5.5–7.5	5.0–7.0	6.0–8.0	4.0–6.0	30–7.0
Copper	1.5–2.5	0.70–1.20	1.5–2.5	1.0–2.4	1.0–1.4
Manganese	1.0–2.0	1.0 max	1.0 max	1.5 max	2.0 max
Cobalt, max	2.5	...	5.0 max	5.0 max	...
Carbon, max	0.05	0.03	0.015 max	0.03 max	0.015
Tungsten	1.0 max	...	1.5 max	1.5–4.0	...
Silicon, max	1.0	1.0	1.0 max	0.8 max	0.3
Phosphorus, max	0.04	0.03	0.04 max	0.04 max	0.020
Sulfur, max	0.03	0.03	0.03 max	0.02 max	0.010
Columbium + tantalum	1.75–2.50	...	0.50 max	0.30–1.50	...
Titanium	...	0.7–1.5
Nitrogen	0.15–0.25

^ASee 13.1.1.

TABLE 2 Mechanical Property Requirements

Alloy	Specified Diameter, in. (mm)	Tensile Strength min, psi (MPa)	Yield Strength (0.2 % Offset), min, psi (MPa)	Elongation in 2 in. or 50.8 mm or 4D ^A min
N06007	5/16 to 3/4 (7.94 to 19.05), incl	90 000 (621)	35 000 (241)	35
	Over 3/4 to 3 1/2 (19.05 to 88.9), incl	85 000 (586)	30 000 (207)	30
N06975	5/16 to 3 1/2 (7.94 to 88.9), incl	85 000 (586)	32 000 (221)	40
N06985	5/16 to 3/4 (7.9 to 19.05), incl	90 000 (621)	35 000 (241)	45
	Over 3/4 to 3 1/2 (19.05 to 88.9), incl	85 000 (586)	30 000 (207)	35
N06030	...	85 000 (586)	35 000 (241)	30
N08031	All sizes	94 000 (648)	40 000 (276)	40

^AD refers to the diameter of the tension specimen.

TABLE 3 Permissible Variations in Diameter and Out-of-Roundness of Rods

Specified Diameter, in. (mm)	Permissible Variations, in. (mm)		
	Diameter		Out-of-Roundness, max
	+	–	
Hot-Finished, Annealed, and Descaled Rods			
5/16 to 7/16 (7.94 to 11.11), incl	0.012 (0.305)	0.012 (0.305)	0.018 (0.457)
Over 7/16 to 5/8 (11.11 to 15.87), incl	0.014 (0.355)	0.014 (0.355)	0.020 (0.508)
Over 5/8 to 3/4 (15.87 to 19.05), excl	0.016 (0.406)	0.016 (0.406)	0.024 (0.610)
Hot-Finished, Annealed, and Ground or Turned Rods			
3/4 to 3 1/2 (19.05 to 88.9), incl	0.010 (0.254)	0	0.008 (0.203)

TABLE 4 Permissible Variations in Length of Rods

Random mill lengths	2 to 12 ft (61 to 366 cm) long with not more than 25 weight % under 4 ft (122 cm).
Multiple lengths	Furnished in multiples of a specified unit length, within the length limits indicated above. For each multiple, an allowance of 1/4 in. (6.35 mm) will be made for cutting, unless otherwise specified. At the manufacturer's option, individual specified unit lengths may be furnished.
Nominal lengths	Specified nominal lengths having a range of not less than 2 ft (61 cm) with no short lengths allowed.
Cut lengths	A specified length to which all rods will be cut with a permissible variation of + 1/8 in. (3.17 mm), – 0.

8.2 *Machining Allowances*—When the surfaces of finished material are to be machined, the following allowances are suggested for normal machining operations:

8.2.1 *As-Finished Rounds (Annealed and Descaled)*—For diameters of 5/16 to 1 1/16 in. (7.94 to 17.46 mm) incl, an allowance of 1/16 in. (1.59 mm) on the diameter should be made for finish machining.

8.3 *Length*—The permissible variations in length of finished rods shall be as prescribed in Table 4. Unless otherwise specified, random mill lengths shall be furnished. Rods ordered to random or nominal lengths shall be furnished with either cropped or saw-cut ends; material ordered to cut lengths shall be furnished with square saw-cut or machined ends. Where rods are ordered in multiple lengths, a 1/4-in. (6.35-mm) length addition shall be allowed for each uncut multiple length.

8.4 *Weight*—For calculation of mass or weight, the following densities shall be used:

8. Permissible Variations in Dimensions

8.1 *Diameter*—The permissible variations from the specified diameter and out-of-roundness shall be as prescribed in Table 3.

Alloy	lb/in. ³	Density g/cm ³
N06007	0.300	8.31
N06975	0.295	8.17
N06985	0.300	8.31



N06030
N08031

0.297
0.293

8.22
8.10

9. Workmanship, Finish, and Appearance

9.1 The material shall be uniform in quality and condition, smooth, commercially straight, and free of injurious imperfections.

10. Sampling

10.1 *Lots for Chemical Analysis and Mechanical Testing:*

10.1.1 A lot for chemical analysis shall consist of one heat.

10.1.2 A lot of rod for mechanical testing shall be defined as the material from one heat in the same condition and specified thickness.

10.2 *Sampling for Chemical Analysis:*

10.2.1 A representative sample shall be obtained from each lot during pouring or subsequent processing.

10.2.2 Product (check) analysis shall be wholly the responsibility of the purchaser and shall conform to the product (check) analysis variations per Specification B 880.

10.3 *Sampling for Mechanical Testing:*

10.3.1 A representative sample shall be taken from each lot of finished material.

11. Number of Tests and Retests

11.1 *Chemical Analysis*—One test per lot.

11.2 *Tension Tests*—One test per lot.

11.3 *Retests*—If the specimen used in the mechanical test of any lot fails to meet the specified requirements, two additional specimens shall be taken from different sample pieces and tested. The results of the tests on both of these specimens shall meet the specified requirements.

12. Specimen Preparation

12.1 Tension test specimens shall be taken from material after final heat treatment and tested in the direction of fabrication.

12.2 Tension test specimens shall be any of the standard or subsized specimens shown in Test Methods E 8.

12.3 In the event of disagreement, the referee specimen shall be the largest possible round specimen shown in Test Methods E 8.

13. Test Methods and Chemical Analysis

13.1 The chemical composition and mechanical properties of the material as enumerated in this specification shall be determined, in case of disagreement, in accordance with the following ASTM methods:

13.1.1 *Chemical Analysis*—Test Methods E 1473. For elements not covered by Test Methods E 1473, the referee method

shall be as agreed upon between the manufacturer and purchaser. The composition of the remainder element shall be determined arithmetically by difference.

13.1.2 *Tension Test*—Test Methods E 8.

13.1.3 *Method of Sampling*—Practice E 55.

13.1.4 *Determining Significant Places*—Practice E 29.

13.2 For purposes of determining compliance with the limits in this specification, an observed value or a calculated value shall be rounded in accordance with the rounding method of Practice E 29:

Requirements	Rounded Unit for Observed or Calculated Value
Chemical composition and tolerances	nearest unit in the last right-hand place of figures of the specified limit
Tensile strength and yield strength	nearest 1000 psi (7 MPa)
Elongation	nearest 1 %

14. Inspection

14.1 Inspection of the material shall be made as agreed upon by the manufacturer and the purchaser as part of the purchase contract.

15. Rejection and Rehearing

15.1 Material that fails to conform to the requirements of this specification may be rejected. Rejection should be reported to the producer or supplier promptly and in writing. In case of dissatisfaction with the results of the test, the producer or supplier may make claim for a rehearing.

16. Certification

16.1 When specified in the purchase order or contract, a manufacturer's certification shall be furnished to the purchaser stating that material has been manufactured, tested, and inspected in accordance with this specification, and that the test results on representative samples meet specification requirements. When specified in the purchase order or contract, a report of the test results shall be furnished.

17. Product Marking

17.1 Each piece of material ½ in. (12.7 mm) and over in diameter shall be marked with this specification number, name of the material, and size of the product.

17.2 Each bundle or shipping container shall be marked with the name of the material; this specification number; alloy; the size; gross, tare and net weight; consignor and consignee address; contract or other number; or such other information as may be defined in the contract or order.

18. Keywords

18.1 rod; N06007; N06975; N06985; N06030; N08031

APPENDIX**(Nonmandatory Information)****X1. HEAT TREATMENT**

X1.1 Proper heat treatment during or subsequent to fabrication is necessary for optimum performance and the manufacturer shall be consulted for details.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).