

Methods of test for

Aluminium oxide —

Part 18: Determination of phosphorus content

[ISO title: Aluminium oxide primarily used for the production of aluminium — Determination of phosphorus content — Reduced phosphomolybdate spectrophotometric method]

NOTE It is recommended that this Part be read in conjunction with the general information given in BS 4140-0 “General introduction” which is issued separately.

UDC 661.862.22:546.18:543.42

This British Standard, having been prepared under the direction of the Chemicals Standards Committee, was published under the authority of the Executive Board and comes into effect on 28 February 1986

© BSI 10-1999

The following BSI references relate to the work on this standard:
 Committee reference CIC/24
 Draft for comment 85/52367 DC

ISBN 0 580 15015 1

Amendments issued since publication

Amd. No.	Date of issue	Comments

Contents

	Page
National foreword	ii
<hr/>	
1 Scope and field of application	1
2 Reference	1
3 Principle	1
4 Reagents	1
5 Apparatus	2
6 Procedure	2
7 Expression of results	3
8 Test report	3
<hr/>	
Publication referred to	Inside back cover

National foreword

This Part of BS 4140 is identical with ISO 2829:1973 “*Aluminium oxide primarily used for the production of aluminium — Determination of phosphorus content — Reduced phosphomolybdate spectrophotometric method*”, published by the International Organization for Standardization (ISO).

The method supersedes clause 18 of Addendum No. 3 (1974) to BS 4140:1967. Parts 17 to 19 of this standard collectively supersede Addendum No. 3 (1974) to BS 4140:1967 which is withdrawn.

Terminology and conventions. The text of the International Standard has been approved as suitable for publication as a British Standard without deviation.

Some terminology and certain conventions are not identical with those used in British Standards; attention is drawn especially to the following.

The comma has been used as a decimal marker. In British Standards it is current practice to use a full point on the baseline as the decimal marker.

In British Standards it is current practice to use the symbol “L” for litre (and its submultiples) rather than “l”.

Wherever the words “International Standard” appear, referring to this standard, they should be read as “British Standard”.

Cross-reference

International Standard	Corresponding British Standard
ISO/R 804:1968 (Revised as ISO 804:1976)	BS 4140 <i>Methods of test for aluminium oxide</i> Part 4:1986 <i>Preparation of sample solution by alkaline fusion</i> (Identical)

This standard prescribes methods of test only, and should not be used or quoted as a specification defining limits of purity. Reference to this Part should indicate that the method of test used complies with BS 4140-18:1986.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, pages i and ii, pages 1 to 4, an inside back cover and a back cover.

This standard has been updated (see copyright date) and may have had amendments incorporated. This will be indicated in the amendment table on the inside front cover.

1 Scope and field of application

This International Standard specifies a spectrophotometric method using reduced ammonium phosphomolybdate for the determination of the phosphorus content of aluminium oxide primarily used for the production of aluminium.

The method is applicable to phosphorus contents, expressed as P_2O_5 , greater than 0,000 5 %.

2 Reference

ISO/R 804, *Aluminium oxide primarily used for the production of aluminium — Preparation of sample solution for analysis*.

3 Principle

Preparation of a solution from a test portion by alkaline fusion, either with a mixture of sodium carbonate and boric acid, or with a mixture of sodium carbonate and sodium tetraborate. Dissolution of the melt in nitric acid and adjustment of an appropriate aliquot portion to pH 2.

Formation of the phosphomolybdic complex and extraction by 2-methylpropan-1-ol in a sulphuric acid medium.

Reduction of the complex by tin(II) chloride in the organic phase and spectrophotometric measurement of the reduced complex contained in the organic phase at a wavelength of about 730 nm.

4 Reagents

Distilled water, or water of equivalent purity, shall be used in the test.

4.1 Sodium carbonate, anhydrous.

4.2 Boric acid (H_3BO_3), or alternatively

4.2.1 Sodium tetraborate, anhydrous ($Na_2B_4O_7$).

4.3 2-Methylpropan-1-ol (isobutyl alcohol), ρ approximately 0,805 g/ml.

4.4 Nitric acid, approximately 8 N solution.

Dilute 540 ml of nitric acid solution, ρ approximately 1,40 g/ml, about 68 % (m/m) solution, with water to 1 000 ml.

4.5 Sulphuric acid, approximately 10 N solution.

Carefully add, in small portions, 280 ml of sulphuric acid, ρ approximately 1,84 g/ml, about 96 % (m/m) solution, to about 500 ml of water and, after cooling, dilute to 1 000 ml.

4.6 Sulphuric acid, approximately N solution.

Take 100 ml of the sulphuric acid solution (4.5) and dilute with water to 1 000 ml.

4.7 Sulphuric acid, approximately 0,5 N solution.

Take 250 ml of the sulphuric acid solution (4.6) and dilute with water to 500 ml.

4.8 Ammonium acetate, 500 g/l solution.

4.9 Iron(III) sulphate, acid solution.

Dissolve 0,5 g of iron(III) sulphate nonahydrate [$Fe_2(SO_4)_3 \cdot 9H_2O$] in 50 ml of water containing 2 ml of perchloric acid solution, ρ approximately 1,60 g/ml, about 64,5 % (m/m) solution, and dilute to 100 ml.

1 ml of this solution contains about 0,001 g of Fe(III).

NOTE If iron(III) sulphate nonahydrate of recognized analytical reagent quality is not available, ammonium iron(III) sulphate dodecahydrate may be used. In this case, to obtain a solution with the same concentration of iron(III), dissolve, instead of 0,5 g of iron(III) sulphate nonahydrate, 0,86 g of ammonium iron(III) sulphate dodecahydrate [$FeNH_4(SO_4)_2 \cdot 12H_2O$].

4.10 Ammonium iron(II) sulphate, acid solution.

Dissolve 0,5 g of ammonium iron(II) sulphate hexahydrate [$Fe(NH_4)_2(SO_4)_2 \cdot 6H_2O$] in 50 ml of water containing 0,5 ml of perchloric acid solution, ρ approximately 1,60 g/ml, about 64,5 % (m/m) solution, and dilute to 100 ml.

1 ml of this solution contains about 0,000 7 g of Fe(II).

Prepare this solution just before use.

4.11 Ammonium molybdate, 25 g/l acid solution.

Dissolve 5 g of ammonium molybdate tetrahydrate [$(NH_4)_6Mo_7O_{24} \cdot 4H_2O$] in water at 60 °C. Cool and dilute to 100 ml. Add to the solution 100 ml of the sulphuric acid solution (4.5) and mix.

Store the solution in a plastics bottle.

4.12 Washing solution

Saturate, at ambient temperature, approximately 500 ml of the sulphuric acid solution (4.7) with the 2-methylpropan-1-ol (4.3).

4.13 Tin(II) chloride, 2,38 g/l hydrochloric solution.

Dissolve 1,19 g of tin(II) chloride dihydrate ($SnCl_2 \cdot 2H_2O$) in 85 ml of hydrochloric acid solution, ρ approximately 1,19 g/ml, about 38 % (m/m) solution, dilute to 500 ml and transfer the solution into a plastics bottle.

Prepare this solution just before use.

4.14 Phosphorus standard solution corresponding to 0,400 g of P_2O_5 per litre.

Weigh, to the nearest 0,000 1 g, 0,766 8 g of anhydrous potassium dihydrogen phosphate (KH_2PO_4), previously dried over about 12 N sulphuric acid. Dissolve in water, quantitatively transfer the solution into a 1 000 ml one-mark volumetric flask, dilute to the mark and mix.

1 ml of this standard solution contains 0,4 mg of P_2O_5 .

4.15 Phosphorus standard solution corresponding to 0,010 g of P_2O_5 per litre.

Place 25,0 ml of the standard phosphorus solution (4.14) in a 1 000 ml one-mark volumetric flask, dilute to the mark and mix.

1 ml of this standard solution contains 0,01 mg of P_2O_5 .

4.16 Phosphorus standard solution corresponding to 0,001 0 g of P_2O_5 per litre.

Place 25,0 ml of the standard phosphorus solution (4.15) in a 250 ml one-mark volumetric flask, dilute to the mark and mix.

1 ml of this standard solution contains 0,001 mg of P_2O_5 .

5 Apparatus

Ordinary laboratory apparatus and

5.1 Apparatus specified in ISO/R 804

5.2 Burette, graduated in 0,05 ml divisions (see ISO/R 385).

5.3 Separating funnels, 200 ml, with ground glass stoppers.

5.4 pH meter, fitted with a glass electrode.

5.5 Spectrophotometer

NOTE All glassware, including the reagent bottles, shall be of borosilicate or other quality of glass unaffected by phosphorus. Alternatively, plastics apparatus may be used. Wash all the glassware carefully with about 6 N hydrochloric acid solution, then rinse thoroughly with water.

6 Procedure

6.1 Preparation of the test solution (principal solution P).

Using the apparatus specified in 5.1, follow the instructions given in clauses 5.1, 5.2 and 5.3 of ISO/R 804, to give a volume of 250 ml of principal solution P.

6.2 Blank test

At the same time as the determination, carry out a blank test in the absence of the pure aluminium oxide, according to the instructions of clause 5.4.2 of ISO/R 804. Then proceed using the same quantities of all reagents used for the determination and following the same procedure.

6.3 Preparation of the calibration curve

6.3.1 Preparation of standard colorimetric solutions, referring to spectrophotometric measurements made with an optical path length of 1 cm.

6.3.1.1 TAKING ALIQUOT PORTIONS OF THE STANDARD SOLUTION

Into a series of six of the separating funnels (5.3) measure, by means of the burette (5.2), the volumes of the standard phosphorus solution (4.16) shown in the following table:

Standard phosphorus solution (4.16)	Corresponding mass of P_2O_5
ml	mg
0 ^a	0
5,0	0,005
10,0	0,010
15,0	0,015
20,0	0,020
25,0	0,025

^a Compensation solution.

Add to each separating funnel the quantity of water required to increase the volume to 60 ml, then add 1 ml of the iron(III) sulphate solution (4.9) and 1 ml of the ammonium iron(II) sulphate solution (4.10) to each funnel and mix.

6.3.1.2 FORMATION OF THE OXIDIZED PHOSPHOMOLYBDATE COMPLEX AND EXTRACTION OF THE REDUCED COMPLEX

Add to each separating funnel 3 ml of the sulphuric acid solution (4.6), then 7,5 ml of the ammonium molybdate solution (4.11), mix and leave to stand for 10 min. Add 25 ml of the 2-methylpropan-1-ol (4.3) and shake vigorously for 1 min. Allow the layers to separate, run off the aqueous phase and discard it. To the organic phase add 30 ml of the washing solution (4.12), shake for 1 min, run off the aqueous phase and discard it. Repeat this washing once more.

Then add 30 ml of the sulphuric acid solution (4.6) and 0,5 ml of the tin(II) chloride solution (4.13), shake for 30 s, allow to settle, run off the aqueous phase and discard it.

Transfer the organic phase to a 25 ml one-mark volumetric flask which has been previously dried. Wash the separating funnel with 1 to 2 ml of the 2-methylpropan-1-ol (4.3), transferring the washings to the same volumetric flask. Then dilute to the mark with the same 2-methylpropan-1-ol (4.3). Mix and leave to stand, shielded from light, for at least 10 min.

6.3.2 Spectrophotometric measurements

After allowing to stand for at least 10 min but not more than 60 min, carry out the spectrophotometric measurements using the spectrophotometer (5.5) at a wavelength of about 730 nm after having adjusted the instrument to zero absorbance against the compensation solution.

6.3.3 Preparation of the calibration chart

Plot a graph having, for example, the values, expressed in milligrams, of the masses of P_2O_5 per 25 ml of the standard colorimetric solutions on the abscissae and the corresponding values of absorbance on the ordinates.

6.4 Determination

6.4.1 Treatment of the test solution

Take a volume of the test solution (6.1) containing a mass of phosphorus corresponding to 0,015 to 0,025 mg of P_2O_5 . Adjust the pH to $2 \pm 0,1$ by the addition, in small portions, of the ammonium acetate solution (4.8), checking by means of the pH meter (5.4). Transfer the solution quantitatively to one of the separating funnels (5.3).

Increase the volume of the solution to about 60 ml and then add 1 ml of the iron(III) sulphate solution (4.9), 1 ml of the ammonium iron(II) sulphate solution (4.10) and mix.

6.4.2 Formation of the oxidized phosphomolybdic complex and extraction of the reduced complex

Follow the instructions in 6.3.1.2.

6.4.3 Spectrophotometric measurements

Carry out the spectrophotometric measurements on the organic phase resulting from the test solution and on that originating from the blank test solution, according to the instructions in 6.3.2, after having adjusted the spectrophotometer (5.5) to zero absorbance against the 2-methylpropan-1-ol (4.3).

7 Expression of results

By means of the calibration chart (6.3.3), determine the mass of P_2O_5 corresponding to the absorbance values.

The phosphorus pentoxide content (P_2O_5) is given, as a percentage by mass, by the formula

$$\frac{(m_1 - m_2) \times D \times 100}{1\,000 \times m_0} = \frac{(m_1 - m_2) \times D}{10 \times m_0}$$

where

m_0 is the mass, in grams, of the test portion used for the preparation of the principal solution P;

m_1 is the mass, in milligrams, of P_2O_5 found in the aliquot portion of the test solution;

m_2 is the mass, in milligrams, of P_2O_5 found in a corresponding aliquot portion of the blank test solution;

D is the ratio of the volume of the principal solution P to the volume of the aliquot portion of this solution taken for the determination.

8 Test report

The test report shall include the following particulars:

- the reference of the method used;
- the results and the method of expression used;
- any unusual features noted during the determination;
- any operation not included in this International Standard or the document to which reference is made, or regarded as optional.

Publication referred to

See national foreword.

BS 4140-18:
1986
ISO 2829:1973

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: 020 8996 9000. Fax: 020 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: 020 8996 9001. Fax: 020 8996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: 020 8996 7111. Fax: 020 8996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: 020 8996 7002. Fax: 020 8996 7001.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager.
Tel: 020 8996 7070.

BSI
389 Chiswick High Road
London
W4 4AL