



Standard Test Method for Sulfur in Graphite by Combustion-Iodometric Titration Method¹

This standard is issued under the fixed designation C 816; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

ε¹ NOTE—Section 11 was added editorially in April 1998.

1. Scope

1.1 This test method covers the determination of sulfur in graphite in the concentration range from 1 to 200 µg/g in a 1-g sample or 5 to 1000 µg/g in a 0.2-g sample.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

D 3177 Test Method for Total Sulfur in the Analysis Sample of Coal and Coke²

E 50 Practices for Apparatus, Reagents, and Safety Precautions for Chemical Analysis of Metals³

3. Summary of Test Method

3.1 The sample is burned in oxygen and a major portion of the sulfur is converted to sulfur dioxide. The sulfur dioxide is passed through a potassium iodide-starch solution where it is titrated with potassium iodate solution. The potassium iodate solution is standardized against samples of known sulfur content.

4. Significance and Use

4.1 Sulfur, even in very low concentrations, is of concern in a nuclear reactor because of potential corrosion of metallic components. This test method has the sensitivity to analyze very low sulfur contents in graphite using very small samples.

4.2 This test method can be used to characterize graphite for design purposes.

5. Interferences

5.1 Any substance that releases volatile material, which tends to enhance or to bleach the starch-iodine complex, will interfere. Halogens and oxides of nitrogen interfere through darkening the color of the starch-iodine complex. Ultraviolet light will also darken the solution. A tube packed with either silver wool or antimony filings placed in the line between the furnace and titration assembly will remove halogens from the gas stream.

5.2 If the solution in the titration vessel becomes colorless during the titration, some SO₂ will be lost and a low result will be obtained for the sulfur content.


6. Apparatus

6.1 Apparatus for the determination of sulfur by direct combustion shall be in accordance with No. 13 in Fig. 13 of Practices E 50⁴.

7. Reagents and Materials

7.1 *Potassium Iodate Solution* (0.0444 g/L)—Dissolve 0.0444 g of potassium iodate (KIO₃) in water and dilute to 1 L.

NOTE 1—The sulfur equivalent for the KIO₃ solution is based on the following reactions:



On the basis of 100 % conversion of sulfur to SO₂, 1 mL of this solution is equivalent to 20 µg of sulfur.

7.2 *Hydrochloric Acid*—Dilute 15 mL of concentrated hydrochloric acid (HCl, sp gr 1.19) to 1 L with water.

7.3 *Starch-Potassium Iodide Solution*—Add 2 g of arrow-root starch to 50 mL of water. Separately boil 150 mL of water and slowly add the starch solution, stirring constantly. Cool, add 6 g of potassium iodide (KI), and pour the resulting solution into a flask. Store in a refrigerator.

¹ This test method is under the jurisdiction of ASTM Committee D02 on Petroleum Products and Lubricants and is the direct responsibility of Subcommittee D02.F on Manufactured Carbon and Graphite Products.

Current edition approved July 26, 1985. Published September 1985. Originally published as C 816 – 77. Last previous edition C 816 – 77.

² *Annual Book of ASTM Standards*, Vol 05.06.

³ *Annual Book of ASTM Standards*, Vol 03.05.

⁴ Equipment found suitable for this method is available from Laboratory Equipment Co., St. Joseph, MI.

7.4 *Standard Sulfur*—Prepare sulfur standards from coke samples that have been analyzed by the Eschka Method in accordance with Test Method D 3177.

8. Procedure

- 8.1 Adjust the furnace temperature to 1400 to 1425°C.
- 8.2 Turn on the oxygen and set the flow to 1 L/min.
- 8.3 Fill the buret with the iodate solution.
- 8.4 Rinse the titration vessel with HCl solution and drain.
- 8.5 Fill the SO₂ titration vessel to the operating level with HCl solution.
- 8.6 Add 2 mL of the starch-KI solution to the titration vessel.
- 8.7 Adjust the color of the solution in the titration vessel to a medium blue by additions of small amounts of KIO₃ solution. This color will be the color of the end point.

NOTE 2—If using a commercial sulfur titrator, follow the manufacturer's instructions for its operation.

- 8.8 Remove the stopper from the mouth of the combustion tube. Insert a boat containing a 0.2 to 1.0 g sample into the combustion tube and push into the hot zone.

NOTE 3—Furnace tubes used for high sulfur samples (above 1000 ppm S) should not be used for low sulfur samples. Separate furnace tubes should be used for low and high sulfur samples.

- 8.9 Replace the stopper sending the flow of oxygen through the combustion tube.
- 8.10 Titrate the solution with the KIO₃ solution to maintain the blue color developed in 8.7.
- 8.11 When the combustion of the sample is complete, record the volume of KIO₃ solution used for the titration.
- 8.12 Make a blank run on an empty prefired boat, igniting for the same length of time as the sample.

8.13 Run standard sulfur samples to obtain a calibration factor. Place a weighed amount of the standard in a prefired boat, ignite, and titrate following steps 8.9 to 8.12.

9. Calculation

- 9.1 Calculate the sulfur factor as follows:

$$F = S/(R-B)$$

where:

- F = sulfur factor,
 S = amount of sulfur in the standard, µg,
 R = amount of titrant for the standard, mL, (Note 4), and,
 B = amount of titrant for the blank, mL, (Note 4).

NOTE 4—Or substitute the apparent percentage of sulfur for “direct reading” burets.

- 9.2 Calculate the amount of sulfur in the test sample as follows:

$$\text{Sulfur, ppm} = [(T-B) \times F]/G$$

where:

- T = amount of titrant for the sample, L, (Note 4),
 B = amount of titrant for the blank, mL, (Note 4),
 F = sulfur factor, and
 G = amount of sample, g.

10. Precision and Bias

- 10.1 The reproducibility among four laboratories was 14 % at the 9-ppm level and 4.2 % at the 86-ppm level.

11. Keywords

- 11.1 combustion; graphite; sulfur; titration

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).