



## Standard Practice for Determining Metric Dimensions of Standard Series Refractory Brick and Shapes<sup>1</sup>

This standard is issued under the fixed designation C 861; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This practice lists dimensions in millimetres for standard series refractory brick and shapes of all compositions.

1.2 A standard method for converting all other dimensions of shaped refractory articles from inch-pound to SI units is included.

1.3 The values stated in SI units are to be regarded as the standard. The values given in parenthesis are for information only.

### 2. Referenced Documents

2.1 *ASTM Standards:*

IEEE/ASTM SI-10 Standard for Use of the International System of Units (SI): The Modern Metric System

### 3. Significance and Use

3.1 This practice is provided in the interest of facilitating the transition of dimensional practice for standard refractory brick and shapes from inch-pound units to metric (SI) units.

3.2 The standard dimensions are based on a 38-mm module (taken as the equivalent to 1.5 in.) and are developed with the aim of preserving a modular relationship between the dimensions of the principal rectangular refractory shapes.

### 4. Standard Dimensions

4.1 Table 1 lists the standard nominal dimensions in millimetres, with corresponding standard dimensions in inch-pound units shown for reference only. Note that these dimensions are not exact conversions, but in all but two cases are within ¼ % of the exact value.

TABLE 1 Standard Dimensions for Refractory Brick and Shapes

In.	Committee C-8, mm	ISO, <sup>A</sup> mm, min
1¼	32	32
1½	38	38
2½	64	64
3	76	76
4½	114	114
6	152	150
6¾	171	172
9	228	230
12	304	300
13½	342	345
15	380	...
18	456	...

<sup>A</sup>International Standards Organization.

### 5. Conversion

5.1 For dimensions not listed in Table 1, multiply the dimension in inches by the factor 25.4 to obtain the exact conversion in millimetres. For description or specification of refractory shapes, round the dimension to the nearest whole millimetre. For example:

1 in.  $\times$  25.4 = 25.4 mm, expressed as 25 mm

11 in.  $\times$  25.4 = 279.4 mm, expressed as 279 mm

22½ in.  $\times$  25.4 = 571.5 mm, expressed as 572 mm

### 6. Standard Equivalent

6.1 For closest approximation to inch-pound units, the metric (SI) Standard Equivalent is based upon the 228 by 114 by 64-mm straight. One Standard Equivalent thus contains 1.6635 dm<sup>3</sup>(101.51 in.<sup>3</sup>).

NOTE 1—For comparison, the Standard Equivalent in inch-pound units is based on the 9 by 4½ by 2½-in. straight and thus contains 101.25 in.<sup>3</sup>, or 1.6592 dm<sup>3</sup>. The difference, 0.0043 dm<sup>3</sup>(0.26 in.<sup>3</sup>), amounts to a 0.26 % increase over the older value.

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee C-8 on Refractories, and is the direct responsibility of Subcommittee C08.92, the Joseph E. Kopanda Subcommittee for Editorial and Terminology.

Current edition approved Dec. 15, 1993. Published February 1994. Originally published as C 861 – 71. Last previous edition C 861 – 77 (1987)ε<sup>1</sup>.

*The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)).*