



Standard Specification for Steel Plates, 9 % Nickel Alloy, for Pressure Vessels, Produced by the Direct-Quenching Process¹

This standard is issued under the fixed designation A 844/A 844M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers 9 % nickel-alloy steel plates produced by the direct-quenching process. The plates are intended primarily for use in welded pressure vessels.

1.2 The direct-quenching process consists of quenching the plates directly after rolling, without permitting the plates to cool below the critical temperature prior to initiation of the quenching operation, and subsequently tempering the plates. (This differs from the “conventional” process in which the plates are permitted to cool to a temperature significantly below the critical temperature, usually to ambient temperature, prior to reheating to a temperature above the upper critical temperature, then quenching, and subsequently tempering.)

1.3 The maximum nominal thickness of plates furnished under this specification shall not exceed 2 in. [50 mm].

1.4 This material is susceptible to magnetization. Use of magnets in handling after heat treatment should be avoided if residual magnetism would be detrimental to subsequent fabrication or service.

1.5 The values stated in either inch-pound or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

2. Referenced Documents

2.1 ASTM Standards:

A 20/A20M Specification for General Requirements for Steel Plates for Pressure Vessels²

A 435/A435M Specification for Straight-Beam Ultrasonic Examination of Steel Plates²

A 577/A577M Specification for Ultrasonic Angle-Beam Examination of Steel Plates²

¹ This specification is under the jurisdiction of ASTM Committee A-1 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.11 on Steel Plates for Boilers and Pressure Vessels.

Current edition approved June 15, 1993. Published August 1993. Originally published as A 844/A 844M – 85. Last previous edition A 844/A 844M – 87b (1991).

² *Annual Book of ASTM Standards*, Vol 01.04.

A 578/A578M Specification for Straight-Beam Ultrasonic Examination of Plain and Clad Steel Plates for Special Applications²

3. General Requirements and Ordering Information

3.1 Material supplied to this material specification shall conform to Specification A 20/A 20M. These requirements outline the testing and retesting methods and procedures, permissible variations in dimensions, quality and repair of defects, marking, loading, etc.

3.2 Specification A 20/A 20M also establishes the rules for ordering information that should be complied with when purchasing material to this specification.

3.3 In addition to the basic requirements of this specification, certain supplementary requirements are available when additional control, testing, or examination is required to meet end use requirements. These include:

3.3.1 Vacuum treatment,

3.3.2 Additional or special tension testing,

3.3.3 Additional or special impact testing, and

3.3.4 Nondestructive examination.

3.4 The purchaser is referred to the listed supplementary requirements in this specification and to the detailed requirements in Specification A 20/A 20M.

3.5 If the requirements of this specification are in conflict with the requirements of Specification A 20/A 20M, the requirements of this specification shall prevail.

4. Manufacture

4.1 *Steelmaking Practice*—The steel shall be killed and shall conform to the fine austenitic grain size requirement of Specification A 20/A 20M.

4.2 *Heat Treatment*:

4.2.1 The plates shall be quenched directly after rolling, without being allowed to cool below 1205°F [650°C]. The quenching shall be initiated from a temperature within the range from 1205 to 1670°F [650 to 910°C]. (The temperature shall be reported in accordance with 19.2 of Specification A 20/A 20M.)

4.2.2 Subsequent to quenching, the plates shall be tempered within the range from 1050 to 1175°F [565 to 635°C], holding at that temperature for a minimum of 30 min/in. [1.2 min/mm]

of thickness but for not less than 15 min., and then cooling at a rate of not less than 300°F/h [165°C/h], either in air or by quenching in water, to ambient temperature.

4.2.2.1 Prior to the tempering treatment, the plates may be subjected to an intermediate heat treatment consisting of heating to a temperature in the range from 1165 to 1290°F [630 to 700°C], holding at that temperature for a minimum of 1 h/in. (2.4 min/mm) of thickness, but in no case less than 15 min, and then water-quenching to below 300°F [150°C] in the case of plate thicknesses of more than 5/8 in. [16 mm] or cooling in air or water-quenching to below 300°F [150°C] in the case of plate thicknesses of 5/8 in. [16 mm] and under.

NOTE 1—The intermediate heat treatment is for the purpose of enhancing elongation and notch-toughness and for reducing susceptibility to strain-aging embrittlement and temper embrittlement. It may be performed at the option of the material manufacturer or may be specified by the purchaser.

5. Chemical Composition

5.1 The steel shall conform to the chemical requirements shown in Table 1 unless otherwise modified in accordance with Supplementary Requirement S17, Vacuum Carbon-Deoxidized Steel, in Specification A 20/A 20M.

6. Finish

6.1 The plates shall be descaled by the producer prior to shipment.

TABLE 1 Chemical Requirements

Element	Composition, %
Carbon, max ^A	0.13
Manganese, max:	
Heat analysis	0.90
Product analysis	0.98
Phosphorus, max ^A	0.020
Sulfur, max ^A	0.020
Silicon:	
Heat analysis	0.15–0.40
Product analysis	0.13–0.45
Nickel:	
Heat analysis	8.50–9.50
Product analysis	8.40–9.60

^AApplies to both heat and product analyses.

7. Mechanical Requirements

7.1 *Tension Test Requirements*—The material as represented by the tension-test specimens shall conform to the requirements specified in Table 2.

7.1.1 For nominal plate thicknesses of 3/4 in. [20 mm] and under, the 1 1/2 -in. [40-mm] wide rectangular specimen may be used for the tension test and the elongation may be determined in a 2-in. [50-mm] gage length that includes the fracture and shows the greatest elongation.

7.2 *Impact Test Requirements:*

7.2.1 Charpy V-notch impact tests shall be made in accordance with Specification A 20/A 20M.

7.2.2 *Number and Location of Test Coupons*—Two impact tests shall be made from each plate-as-heat-treated, with the test coupons being taken from locations adjacent to the tension test coupons.

7.2.3 *Orientation*—The longitudinal axis of the test specimen shall be transverse to the final rolling direction of the plate.

7.2.4 *Test Temperature*—Unless otherwise specified on the order, the tests shall be conducted at –320°F [–195°C].

7.2.5 *Acceptance Criteria*—Each test specimen shall have a lateral expansion opposite the notch of not less than 0.015 in. [0.381 mm].

8. Marking

8.1 In addition to the marking required in Specification A 20/A 20M, each plate shall be legibly stamped or stenciled, depending upon the ordered thickness, with the letters *DQT* except as otherwise specified in 8.1.1.

8.1.1 When the optional heat treatment permitted in 4.2.2 is performed, the plates shall be marked with the letters *DQTT* instead of *DQT*.

TABLE 2 Tensile Requirements

Tensile strength, ksi [MPa]	100 to 120 [690–825]
Yield strength, min, ksi [MPa]	85 [585]
Elongation in 2 in. [50 mm], min, % ^A	20.0

^ASee Specification A 20/A 20M for elongation adjustments.

SUPPLEMENTARY REQUIREMENTS

Supplementary requirements shall not apply unless specified in the order.

A list of standard supplementary requirements, for use at the option of the purchaser, are included in Specification A 20/A 20M. Several of those that are considered to be suitable for use with this specification are listed below by title. Other tests may be performed by agreement between the supplier and the purchaser.

- S1. Vacuum Treatment,
- S2. Product Analysis,
- S3. Simulated Post-Weld Heat Treatment of Mechanical Test Coupons,
- S6. Drop Weight Test,
- S8. Ultrasonic Examination in Accordance with Specification A 435/A 435M,

- S11. Ultrasonic Examination in Accordance with Specification A 577/A 577M,
- S12. Ultrasonic Examination in Accordance with Specification A 578/A 578M,
- S13. NDT Temperature Determination,
- S14. Bend Test,
- S17. Vacuum Carbon-Deoxidized Steel,

S18. Unspecified Elements, and

S19. Restricted Chemical Requirements.

ADDITIONAL SUPPLEMENTARY REQUIREMENTS

Also listed are additional optional Supplementary Requirements S55 and S56 which are suitable for this specification:

S55. Longitudinal Charpy Impact Energy Absorption Requirement:

S55.1 The longitudinal Charpy V-notch impact properties shall not be less than 25 ft·lbf [34 J] at the test temperature specified in the order.

S55.2 Each impact test value shall constitute the average value of three specimens, with not more than one individual specimen value below the specified minimum value of 25 ft·lbf [34 J] but in no case below 20 ft·lbf [27 J] for full-size specimens.

S56. Transverse Charpy Impact Energy Absorption Requirement:

S56.1 The transverse Charpy V-notch impact properties shall not be less than 20 ft·lbf [27 J] at the test temperature specified in the order.

S56.2 Each impact test value shall constitute the average value of three specimens, with not more than one individual specimen value below the specified minimum average value of 20 ft·lbf [27 J] but in no case below 15 ft·lbf [20 J] for full-size specimens.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).