



## Standard Test Method for Determination of Peroxides in Butadiene<sup>1</sup>

This standard is issued under the fixed designation D 5799; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

<sup>ε1</sup> NOTE—Warning notes were placed in the text editorially in November 2000.

### 1. Scope

1.1 This procedure covers the determination of peroxides in butadiene.

1.2 This test method covers the concentrations range of 1 to 10 ppm by mass (ppmw) as available oxygen.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:

D 1265 Practice for Sampling Liquefied Petroleum (LP) Gases—Manual Method<sup>2</sup>

D 3700 Practice for Containing Hydrocarbons Fluid Samples Using a Floating Piston Cylinder<sup>3</sup>

### 3. Summary of Test Method

3.1 A known mass of the butadiene sample is placed in a flask and evaporated. The residue is then refluxed with acetic acid and sodium iodide reagents. The peroxides react to liberate iodine which is titrated with standard sodium thiosulfate solution using visual end-point detection. Interfering traces of iron are complexed with sodium fluoride.

### 4. Significance and Use

4.1 Due to the inherent danger of peroxides in butadiene, specification limits are usually set for their presence. This test method will provide values that can be used to determine the peroxide content of a sample of commercial butadiene.

4.2 Butadiene polyperoxide is a very dangerous product of the reaction between butadiene and oxygen that can occur. The peroxide has been reported to be the cause of some violent explosions in vessels that are used to store butadiene.

### 5. Apparatus

5.1 *Condensers*, Liebig, with 24/40 standard-tapered ground-glass joint connections.

5.2 *Cylinders*, graduated, 100-mL capacity.

5.3 *Flask*, Erlenmeyer, 250-mL capacity, with 24/40 standard-tapered ground-glass connections with marking at 100 mL.

5.4 *Heating Mantle*, electric for 250-mL Erlenmeyer flasks.

5.5 *Microburette*, 10-mL capacity, graduated in 0.02-mL divisions.

5.6 *Water Bath*, a thermostatically controlled liquid bath capable of maintaining a water temperature of  $60 \pm 1^\circ\text{C}$  ( $140 \pm 2^\circ\text{F}$ ).

### 6. Reagents

6.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.<sup>4</sup> Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

6.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean deionized or distilled water.

6.3 *Acetic Acid*, 94 % by volume. Mix 60 mL of water with 940 mL of glacial acetic acid ( $\text{CH}_3\text{COOH}$ ). (**Warning**—Poisonous and corrosive. Combustible. May be fatal if swallowed. Causes severe burns. Harmful if inhaled.)

6.4 *Carbon Dioxide*, solid (dry ice). (**Warning**—Use gloves to avoid frostbite when handling.)

6.5 *Potassium Dichromate Solution, Standard (0.1 N)*—Dissolve 2.452 g of potassium dichromate ( $\text{K}_2\text{Cr}_2\text{O}_7$ ) in water

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D02 on Petroleum Products and Lubricants and is the direct responsibility of Subcommittee D02.D on Hydrocarbons for Chemical and Special Uses.

Current edition approved Oct. 10, 1995. Published December 1995.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 05.01.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 05.02.

<sup>4</sup> *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

and dilute to 500 mL in a volumetric flask. (**Warning**—Avoid contact with eyes and skin and avoid breathing of dust.)

6.6 *Sodium Fluoride.*

6.7 *Sodium Iodide.*

6.8 *Sodium Thiosulfate Solution, Standard (0.1 N)*—Dissolve 12.5 g of sodium thiosulfate ( $\text{Na}_2\text{S}_2\text{O}_3 \times 5\text{H}_2\text{O}$ ) plus 0.1 g of sodium carbonate ( $\text{Na}_2\text{CO}_3$ ) in 500 mL of water (the  $\text{Na}_2\text{CO}_3$  is added to stabilize the  $\text{Na}_2\text{S}_2\text{O}_3$  solution). Let this solution stand a week or more before using. Standardize against 0.1 N  $\text{K}_2\text{Cr}_2\text{O}_7$  solution. Restandardize at frequencies to detect changes of 0.0005 in normality.

## 7. Sampling

7.1 Butadiene should be sampled in a metal container of a type which ensures maximum safety and which is resistant to butadiene corrosion. The size of the container is dependent upon the number of times the test is to be performed according to this test method. Refer to Practice D 1265 or Practice D 3700 for instructions on sampling.

## 8. Procedure

8.1 Remove the oxygen from a 250-mL Erlenmeyer flask by adding several pellets (approximately 1 cm in size) of dry ice and allowing the  $\text{CO}_2$  to displace the air. This will take approximately 5 min.

8.2 Record the weight to one decimal place of the sample cylinder, and then transfer approximately 100 mLs of butadiene sample from the cylinder to the 250 mL Erlenmeyer flask containing several pellets of dry ice. Reweigh the sample cylinder and record the weight of the sample as the difference of the two weights. (**Warning**—Butadiene is a flammable gas under pressure.)

8.3 Place the flask in a water bath at  $60^\circ\text{C}$  in a well ventilated hood. Allow the butadiene to evaporate while keeping an inert atmosphere above the liquid butadiene by continuing to add pellets of dry ice at intervals until all the butadiene has evaporated. (**Warning**—Peroxides are unstable and react violently when taken to dryness. Peroxides at the levels experienced during the test method evaluation have not caused a problem, but caution needs to be exhibited in handling by the use of personal protective equipment.)

8.4 Remove the flask from the water bath and allow to cool to ambient temperature. Add 50 mL of 94 % acetic acid and  $0.20 \pm 0.02$  g of sodium fluoride. Add several more pellets of dry ice to the flask and allow to stand for 5 min.

8.5 Add  $6.0 \pm 0.2$  g of sodium iodide to the flask and immediately connect to the Liebig condenser. Turn on the heating mantle and reflux the solution for  $25 \pm 5$  min. Keep the equipment away from strong light during refluxing.

8.6 At the end of the reaction period, turn off the heating mantle and remove the flask with condenser from the mantle.

Immediately add 100 mL of water through the top of the condenser followed by several pellets of dry ice.

8.7 Maintaining an inert atmosphere with  $\text{CO}_2$  pellets, remove the flask from the condenser and allow to cool to ambient temperature. Cold water may be used to assist in this step. Titrate the liberated iodine with 0.1 N sodium thiosulfate until a clear endpoint is reached.

8.8 Repeat 8.4 through 8.7 for the reagent blank.

## 9. Calculation

9.1 Calculate the peroxide content as follows:

$$\text{peroxide, as } \text{O}_2, \text{ ppmw} = \frac{(A - B) \times N \times 16\,000}{W} \quad (1)$$

where:

$A$  =  $\text{Na}_2\text{S}_2\text{O}_3$  solution required for titration of the sample, mL,

$B$  =  $\text{Na}_2\text{S}_2\text{O}_3$  solution required for titration of the blank, mL,

$N$  = normality of the  $\text{Na}_2\text{S}_2\text{O}_3$  solution,

$W$  = sample weight, g, and

16 000 = milliequivalents of oxygen.

## 10. Precision and Bias <sup>5</sup>

10.1 *Precision*—The precision of this test method as determined by statistical examination of interlaboratory results is as follows:

10.1.1 *Repeatability*—The difference between two test results obtained by the same operator with the same apparatus under constant operating conditions on identical test materials would, in the long run, in the normal and correct operation of the test method, exceed the following values only in one case of twenty:

$$R = 1.4 \text{ ppmw} \quad (2)$$

10.1.2 *Reproducibility*—The difference between two single and independent results, obtained by different operators working in different laboratories on identical test material, would, in the long run and in the normal and correct operation of the test method, exceed the following values only in one case in twenty.

$$R = 3.4 \text{ ppmw} \quad (3)$$

10.2 *Bias*—As no reliable source of butadiene polyperoxide is available, the actual bias of the test method is unknown; but published data reports that this test method determines 90 % of the polyperoxide.<sup>6</sup>

## 11. Keywords

11.1 butadiene; butadiene polyperoxide; peroxide

<sup>5</sup> Supporting data is available from ASTM Headquarters. Request RR:D02:1372.

<sup>6</sup> For a discussion of the background for this test method, see Mayo, Hendry, Jones, and Scheatzle, *Industrial and Engineering Chemical*, Product Research, Vol 7, 1968, p. 145.

*The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)).*