



Standard Specification for Free-Machining Stainless Steel Plate, Sheet, and Strip¹

This standard is issued under the fixed designation A 895; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers hot-finished or cold-finished plate, sheet, and strip in the more commonly used types of stainless free machining steels designed especially for optimum machinability and for general corrosion and high temperature service. Stainless and heat resisting plate, sheet, and strip other than free machining types are covered in separate specifications.

1.2 The values stated in inch-pound units are to be regarded as the standard.

2. Referenced Documents

2.1 ASTM Standards:

A 370 Test Methods and Definitions for Mechanical Testing of Steel Products²

A 480/A480M Specification for General Requirements for Flat-Rolled Stainless and Heat-Resisting Steel Plate, Sheet, and Strip²

A 751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products²

E 527 Practice for Numbering Metals and Alloys³

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *plate*—material $\frac{3}{16}$ in. (4.8 mm) and over in thickness and over 10 in. (250 mm) in width.

3.1.2 *sheet*—material under $\frac{3}{16}$ in. (5.0 mm) in thickness and 24 in. (600 mm) and over in width.

3.1.3 *strip*—material under $\frac{3}{16}$ in. (5.0 mm) in thickness and under 24 in. (600 mm) in width.

4. Process

4.1 The steel shall be made by one or more of the following processes: electric-arc, electric-induction, or other suitable commercial processes.

4.2 Plate, sheet, and strip may be furnished in one of the conditions listed in Table 1.

TABLE 1 Condition

| Type | Condition A (Annealed) | Condition T (Intermediate Temper) | Condition H (Hard Temper) |
|--------|---------------------------|---|------------------------------|
| 303 | A | ... | ... |
| 303Se | A | ... | ... |
| 416 | A | T | H |
| 416Se | A | T | H |
| 420F | A | ... | ... |
| 420FSe | A | T | ... |
| 430F | A | ... | ... |
| 430FSe | A | ... | ... |

5. Ordering Information

5.1 Orders for material under this specification should include the following information:

5.1.1 Quantity (weight or number of pieces),

5.1.2 Type or UNS designation (Table 2),

5.1.3 Form (Plate, Sheet or Strip),

5.1.4 Condition (Table 2),

5.1.5 Finish (9.2),

5.1.6 Dimensions (thickness, width, and length),

5.1.7 Edge, strip only (see Specification A 480/A 480M),

5.1.8 ASTM designation and date of issue,

5.1.9 Additions to specification or special requirements,

5.1.10 Preparation for delivery, and

5.1.11 Marking requirements.

6. Chemical Composition

6.1 The chemical composition shall conform to the requirements specified in Table 2.

6.2 Methods and practices relating to chemical analysis required by this specification shall be in accordance with Test Methods, Practices, and Terminology A 751.

7. Hardness Requirement

7.1 The material shall conform to the hardness requirements as specified in Table 3.

¹ This specification is under the jurisdiction of ASTM Committee A-1 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.17 on Flat Stainless Steel Products.

Current edition approved Dec. 7, 1989. Published February 1990.

² Annual Book of ASTM Standards, Vol 01.03.

³ Annual Book of ASTM Standards, Vol 01.01.



TABLE 2 Chemical Requirements

| UNS Designation ^A | Chemical Composition, % | | | | | | | | |
|------------------------------|-------------------------|---------------------|----------------|-----------------|---------------------|--------------|-------------|-------------------|--------------------------|
| | Type | Carbon ^B | Manganese, max | Phosphorus, max | Sulfur ^B | Silicon, max | Chromium | Nickel | Other Elements |
| S30300 | 303 | 0.15 | 2.00 | 0.20 | 0.15 min | 1.00 | 17.00–19.00 | 8.00–10.00 | ... |
| S30323 | 303Se | 0.15 | 2.00 | 0.20 | 0.06 | 1.00 | 17.00–19.00 | 8.00–10.00 | Se 0.15 min |
| S41600 | 416 | 0.15 | 1.25 | 0.06 | 0.15 min | 1.00 | 12.00–14.00 | ... | ... |
| S41623 | 416Se | 0.15 | 1.25 | 0.06 | 0.06 | 1.00 | 12.00–14.00 | ... | Se 0.15 min |
| S42020 | 420F | 0.30–0.40 | 1.25 | 0.06 | 0.15 min | 1.00 | 12.00–14.00 | 0.50 ^C | Cu 0.60 max ^C |
| S42023 | 420FSe | 0.20–0.40 | 1.25 | 0.06 | 0.06 | 1.00 | 12.00–14.00 | 0.50 ^C | Cu 0.60 max ^C |
| S43020 | 430F | 0.12 | 1.25 | 0.06 | 0.15 min | 1.00 | 16.00–18.00 | ... | Se 0.15 min |
| S43023 | 430FSe | 0.12 | 1.25 | 0.06 | 0.06 | 1.00 | 16.00–18.00 | ... | Se 0.15 min |

^A New designation established in accordance with ASTM Practice E 527 and SAE J 1086, Practice for Numbering Metals and Alloys (UNS).

^B Maximum unless otherwise noted.

^C At manufacturer's option, reported only when intentionally added.

TABLE 3 Mechanical Test Requirements

| Types | Condition | Hardness (HBN) |
|-------------------------|-----------|----------------|
| 303, 303Se | A | 202 max |
| All (except 303, 303Se) | A | 262 max |
| 416, 416Se and 420FSe | T | 248 to 302 |
| 416 and 416Se | H | 293 to 352 |

7.2 The hardness test shall be determined in accordance with Test Methods and Definitions A 370.

8. General Requirements for Delivery

8.1 Material furnished under this specification shall conform to the applicable requirements of the current edition of Specification A 480/A 480M. In case of conflict, the requirements of this specification shall prevail.

9. Workmanship, Finish, and Appearance

9.1 The material shall be of uniform quality consistent with good manufacturing and inspection practices. The steel quality shall be satisfactory for the production or fabrication of finished parts.

NOTE 1—Free-machining stainless steels may not equal the quality of non-free-machining stainless steels because of the inclusions present to impart free-machining.

9.2 Plates and sheets may be ground to remove surface defects, provided such grinding does not reduce the thickness or width at any point beyond the allowable dimensional tolerances. An iron-free abrasive wheel shall be used for such

grinding and shall be operated at a speed ample to ensure that defective areas are cleanly cut out.

10. Product Marking

10.1 Each sheet, strip, or plate shall be marked on one face, in the locations indicated below with the designation number and its suffix, type, heat number, and the name or mark of the manufacturer. The characters shall be of such size as to be clearly legible. The marking shall be sufficiently stable to withstand normal handling. Unless otherwise specified by the purchaser, the marking, at the producer's option, may be done with: (a) marking fluid, (b) low-stress blunt-nosed-continuous or low-stress blunt-nosed-interrupted-dot die stamp, (c) a vibratory tool with a minimum tip radius of 0.005 in. (0.01 mm), or (d) electrochemical etching.

10.1.1 Flat sheet, strip in cut lengths, and plate shall be marked in two places near the ends or may be continuously line marked along one edge.

10.1.2 Sheet and strip in coils shall be marked near the outside end of the coil. The inside of the coil shall also be marked or shall have a tag or label attached and marked with the information in 10.1. Alternatively, the coils may be continuously line marked.

10.1.3 Material less than ¼ in. (6.4 mm) in thickness shall not be marked with die stamps.

10.2 Marking for identification for U.S. Government procurement shall be in accordance with Specification A 480/A 480M.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).